

Design and Application of Hydrogels as Drug Carriers in Modern Pharmaceuticals: A Comprehensive Review

Ayesha Nawaz¹, Urooj Khalid², Muhammad Fezan Arshad³, Masab Saeed^{*4},
Rehana Shaheen⁵, Hifsa Arif⁶, Syed Azhar Shah Kazmi⁷

¹M.Phil Scholar, Department of Chemistry, Hazara University, Mansehra, 21300-Pakistan.

Email: chemistayesha20@gmail.com

²M.Phil Scholar, Department of Botany, Hazara University Mansehra, 21300-Pakistan.

Email: uroojkhalid381@gmail.com

³PhD Scholar, Department of Biotechnology. Mirpur University of Science and Technology. 10250-Mirpur Azad Jammu & Kashmir.

Email: fezanraja786@yahoo.com

⁴PhD, Department of Chemistry, Hazara University Mansehra, 21300-Pakistan. Corresponding Author Email: masabsaeed@hu.edu.pk

⁵Lecturer, Institute of Allied Health Sciences IAHS, Wah Medical College, 470890-Pakistan.

Email: rehanashaheen54@gmail.com

⁶Department of Microbiology, Hazara University Mansehra, 21300-Pakistan.

Email: hifsa1arif@gmail.com

⁷Department of Botany, Hazara University Mansehra, 21300-Pakistan.

Email: azharshahkazmi@hu.edu.pk

ABSTRACT

Hydrogels are emerging as versatile materials for advanced drug delivery systems, offering significant advantages in controlled and sustained drug release. These polymeric networks are highly biocompatible, biodegradable, and capable of encapsulating both hydrophilic and hydrophobic drugs, making them ideal for a wide range of pharmaceutical applications. This review explores the types of hydrogels, including natural (Chitosan, Sodium Alginate) and synthetic (PEG, PVA) polymers, and their mechanisms of drug release, such as diffusion-controlled, swelling-controlled, and stimuli-responsive release systems. The paper also highlights the applications of hydrogels in oral, topical, injectable, ocular, and cancer drug delivery, emphasizing their ability to improve therapeutic efficacy, enhance patient compliance, and reduce side effects. Furthermore, the challenges related to drug loading efficiency, stability, scalability, and regulatory hurdles are discussed. The review concludes with a reflection on future trends, including smart hydrogels, hybrid and

nanocomposite systems, 3D printing for personalized drug delivery, and the role of hydrogels in personalized medicine. These innovations hold the potential to revolutionize drug delivery systems and provide more effective and tailored treatments for various diseases.

Keywords: Hydrogels, Drug Delivery Systems, Smart Hydrogels, Personalized Medicine, Sustained Release.

1. Introduction

Hydrogels are three-dimensional, cross-linked polymer networks that possess the unique ability to absorb large amounts of water while maintaining their structure [1]. Chemically, hydrogels are composed of hydrophilic polymer chains, which can either be natural or synthetic [2]. The network structure of hydrogels allows them to retain water molecules within their polymer matrix, giving them their characteristic gel-like consistency. Their water content typically ranges from 10% to 99%, and this high water content mimics the natural environment of living tissues, making them highly biocompatible [3]. Due to these properties, hydrogels have found extensive applications in medical and pharmaceutical fields. In pharmaceutical applications, hydrogels have proven to be particularly valuable for controlled drug delivery systems [4]. Their ability to swell and retain water, coupled with their structural flexibility, makes them ideal candidates for encapsulating and releasing pharmaceutical agents in a controlled manner. Hydrogels can be engineered to release drugs in response to environmental stimuli such as pH, temperature, and ionic strength, offering a level of precision that is hard to achieve with traditional drug delivery methods [5].

The need for advanced drug delivery systems has become increasingly important in the treatment of various diseases [6]. Conventional methods, such as oral tablets and injections, often lead to rapid drug release, resulting in fluctuating drug concentrations in the bloodstream. This fluctuation can cause side effects, reduced efficacy, and patient non-compliance. Therefore, there has been a growing demand for systems that can release drugs in a controlled, sustained, and site-specific manner [7]. Hydrogels provide a solution to these challenges by enabling controlled release, which can enhance the therapeutic effectiveness of drugs while minimizing side effects [8]. By designing hydrogels with specific release

mechanisms—such as diffusion, swelling, or stimuli-responsiveness—pharmaceutical formulations can be tailored to meet the specific needs of the patient and the drug [9]. For example, drugs encapsulated in hydrogels can be delivered over extended periods, allowing for consistent therapeutic effects without frequent dosing [10].

Hydrogels have gained significant importance in modern pharmaceuticals due to their ability to improve therapeutic outcomes, target specific sites within the body, and enhance patient compliance [11]. One of the key advantages of hydrogels is their ability to encapsulate both hydrophilic and hydrophobic drugs, providing a versatile platform for drug delivery [12]. This versatility is particularly beneficial for drugs that are otherwise difficult to deliver using traditional methods [13]. For instance, Chitosan and Sodium Alginate-based hydrogels have emerged as promising candidates in the field of drug delivery due to their biocompatibility, biodegradability, and ability to form stable gels. Chitosan, a natural polysaccharide derived from chitin, offers antimicrobial properties and mucoadhesiveness, which make it suitable for oral and topical drug delivery [14]. Sodium Alginate, another natural polymer, is known for its gel-forming properties in the presence of divalent cations, particularly calcium, and is widely used in the design of controlled-release formulations [15]. Chitosan-Sodium Alginate-based hydrogels offer a powerful approach to enhancing drug delivery, allowing for sustained and targeted release [16]. This is particularly important for treating chronic conditions or diseases that require long-term therapy, such as cancer, diabetes, or cardiovascular diseases [17]. The ability to target specific tissues or organs using hydrogels ensures that the drug is delivered precisely where it is needed, minimizing off-target effects and improving the overall efficacy of the treatment. Moreover, hydrogels improve patient compliance by reducing the frequency of drug administration [18]. For example, sustained-release formulations can reduce the need for frequent dosing, which is especially beneficial for elderly patients or those with chronic conditions who may struggle with adhering to complex medication schedules. The ability to design hydrogels that respond to specific physiological conditions, such as pH or temperature, further enhances the specificity and control of drug release.

Objectives of the Review

This review aimed to:

- i. To explore the design and application of Chitosan-Sodium Alginate-based hydrogels as drug carriers in modern pharmaceuticals.
- ii. To investigate the mechanisms of drug release from hydrogels and their impact on controlled drug delivery.
- iii. To examine the current and potential future applications of hydrogels, with an emphasis on their role in improving therapeutic efficacy and patient compliance.

2. Types of Hydrogels

Hydrogels can be classified into two primary categories: natural hydrogels and synthetic hydrogels. Each type offers distinct advantages and is selected based on the specific requirements of the drug delivery system [19]. This section explored the properties, applications, and advantages of natural hydrogels such as Chitosan, Sodium Alginate, and Plant Extracts, as well as synthetic hydrogels like Polyethylene Glycol (PEG) and Polyvinyl Alcohol (PVA), alongside hybrid hydrogels that combine the benefits of both natural and synthetic materials [19].

2.1 Natural Hydrogels

2.1.1 Chitosan

Chitosan is a natural polysaccharide derived from chitin, which is found in the exoskeletons of crustaceans such as shrimp and crabs [14]. It is obtained through the deacetylation process of chitin, making it a biopolymer with a high degree of availability and sustainability [20]. Chitosan is a versatile material with a variety of functional properties, including biodegradability, biocompatibility, and non-toxicity, which make it ideal for pharmaceutical and biomedical applications [21]. Chitosan's chemical structure consists of glucosamine and N-acetylglucosamine units, which are linked by β -(1,4)-glycosidic bonds [22]. Its hydrophilic nature and positive charge at physiological pH contribute to its solubility and mucoadhesive properties [23]. The positive charge of chitosan enhances its ability to bind with negatively charged biological membranes, allowing it to adhere to mucosal surfaces and provide localized drug release. Chitosan is also biodegradable, breaking down into non-toxic products that are eliminated from the body without causing harm [24]. This

property makes it an excellent candidate for controlled and sustained drug delivery. Furthermore, it is biocompatible, meaning it can interact with body tissues without inducing an immune response. These properties are particularly beneficial for drug delivery systems that require gradual degradation, such as in oral or topical formulations [25]. Chitosan has been widely researched and applied in the development of drug delivery systems due to its ability to encapsulate both hydrophilic and hydrophobic drugs. It has been incorporated into formulations for oral drug delivery, especially for targeting the gastrointestinal tract [26]. Chitosan-based hydrogels can protect drugs from enzymatic degradation, ensuring that the drug reaches its target site effectively [27]. In wound healing, Chitosan hydrogels have shown significant potential due to their antimicrobial properties, which prevent infections and accelerate tissue regeneration. Additionally, Chitosan's mucoadhesive properties are particularly valuable for nasal and ocular drug delivery, where prolonged drug retention is essential for therapeutic effectiveness. Cancer therapy has also benefited from Chitosan-based systems, as it can be used for controlled release and targeted drug delivery, minimizing systemic toxicity [28].]




Figure 1: Chitosan (Sources, Structure and applications)

2.1.2 Sodium Alginate

Sodium Alginate is a natural polysaccharide derived from brown seaweed (Figure 2a), particularly from the genera *Laminaria* and *Macrocystis* [29]. It is a salt of alginic acid, and its gel-forming ability is one of the most notable characteristics, making it widely used in pharmaceutical formulations [30]. Sodium Alginate is known for its pH-sensitive behavior, which makes it suitable for designing drug delivery systems that respond to the pH of the environment [31]. When exposed to acidic conditions, such as in the stomach, Sodium Alginate forms a gel that can encapsulate drugs and protect them from gastric acid. In more neutral or basic environments, such as the intestines, the gel can break down to release the drug at a controlled rate [30]. The gelation of Sodium Alginate occurs when the polymer chains interact with divalent cations like calcium ions, forming a three-dimensional network that can trap drug molecules [12]. This network structure enables controlled release, providing a sustained drug release profile over an extended period. Sodium Alginate-based hydrogels are widely used in oral drug delivery systems, particularly for controlled and sustained release. These systems can be designed to release drugs at specific locations, such as in the intestines, where the pH is more neutral. Encapsulation of drugs in Sodium Alginate hydrogels can also protect sensitive drugs from degradation in the acidic gastric environment [31]. Sodium Alginate is also used in topical formulations due to its ability to form hydrogels with desirable viscosity and spreadability, making it ideal for wound care. It can provide a moist environment, which promotes faster healing and minimizes scarring [26].




Figure 2: (a) Sources of Sodium Alginate (b) Extraction of Sodium Alginate

2.1.3 Plant Extracts

Natural plant extracts are often integrated into hydrogels to enhance the therapeutic properties of the formulation (Figure 3). These extracts are rich in bioactive compounds such as alkaloids, flavonoids, and essential oils, which possess various antioxidant, anti-inflammatory, and antimicrobial activities. The incorporation of plant extracts into hydrogels can significantly improve the bioactivity and efficacy of the drug delivery system. Plant extracts can help modulate the release profiles of the drugs, providing a synergistic effect when combined with pharmaceutical agents. For example, anti-inflammatory plant extracts like aloe vera and calendula can be used in hydrogels for topical applications, providing pain relief and promoting faster tissue regeneration. The antioxidant properties of plant extracts can also protect drugs from oxidation, thereby enhancing the stability and shelf-life of hydrogel formulations. Moreover, certain plant extracts can target specific sites in the body, enhancing the site-specific delivery of drugs and improving the overall therapeutic effect [32].




Figure 3: Polysaccharide-based hydrogels containing herbal extracts for wound healing applications [18]

2.2 Synthetic Hydrogels

2.2.1 Polyethylene Glycol (PEG)

Polyethylene Glycol (PEG) is one of the most widely used synthetic hydrogels. It is a hydrophilic polymer with a simple, linear structure consisting of repeating ethylene glycol units [20, 24, 33-35]. PEG is biocompatible, non-toxic, and water-soluble, making it an ideal candidate for a range of pharmaceutical and biomedical applications [20]. PEG's flexibility, solubility in water, and low immunogenicity allow it to be incorporated into drug delivery systems to enhance the bioavailability of drugs, especially those with poor solubility [10]. In addition to its use in controlled release, PEG is also used to modify the pharmacokinetics of drugs by prolonging their half-life in the bloodstream, a process known as PEGylation [36].

PEG-based hydrogels are frequently used for injectable drug delivery, where a precise and sustained release of drugs is required. Additionally, PEG has been combined with other materials to form composite hydrogels that can be used in wound healing, tissue engineering, and cancer therapy. The use of PEGylation in biologics (e.g., proteins or antibodies) has become a common strategy to reduce immunogenicity and improve therapeutic outcomes [37-39].

2.2.2 Polyvinyl Alcohol (PVA)

Polyvinyl Alcohol (PVA) is a synthetic polymer known for its hydrophilic nature, film-forming capabilities, and water-solubility. PVA is used in a variety of pharmaceutical formulations because it is non-toxic, biocompatible, and can be easily cross-linked to form gels with desirable mechanical properties [40]. PVA-based hydrogels have been explored in controlled drug delivery systems, particularly for sustained-release formulations. They are commonly used in ocular drug delivery because of their good adhesion to the eye's surface. Additionally, PVA is used for wound care and skin regeneration, where it provides moisture to the wound and promotes healing [32].

2.3 Combination of Natural and Synthetic Materials

Hybrid hydrogels are developed by combining natural polymers such as Chitosan or Sodium Alginate with synthetic polymers like PEG or PVA [32]. These hybrid materials combine the advantages of both natural and synthetic materials, offering enhanced mechanical strength, drug loading capacity, and controlled drug release profiles. For instance, the combination of Chitosan and PEG results in a hydrogel with excellent biocompatibility and the ability to respond to external stimuli such as pH changes or temperature fluctuations [36]. The synergistic effects of natural and synthetic components allow for the development of hydrogels with improved stability, targeted delivery, and prolonged drug release. Hybrid hydrogels are particularly useful for highly loaded drug formulations and multifunctional applications, including oncology, diabetes treatment, and gene therapy. Their versatility in both topical and systemic drug delivery makes them a promising option for future pharmaceutical applications [41].

3. Mechanisms of Drug Release

Hydrogels are widely recognized for their ability to encapsulate and release drugs in

a controlled and sustained manner. The drug release from hydrogel systems is governed by several mechanisms, which include diffusion-controlled release, swelling-controlled release, stimuli-responsive release, and combination systems. Each mechanism is influenced by the properties of the hydrogel matrix, the drug being delivered, and the physiological environment. This section discusses each of these mechanisms in detail, providing insight into how they function and the factors that affect drug release [42].

3.1 Diffusion-Controlled Release

Diffusion-Controlled Release is one of the most commonly observed mechanisms for drug delivery in hydrogels. In this system, the drug is initially encapsulated within the hydrogel matrix, and its release occurs as a result of the diffusion of the drug molecules through the hydrogel network [20]. The release rate is determined by the concentration gradient between the hydrogel and the surrounding environment, with the drug molecules moving from the area of higher concentration (inside the hydrogel) to an area of lower concentration (the external medium, such as blood or tissue). The size of the drug molecule plays a significant role in its diffusion rate. Smaller molecules generally diffuse more quickly through the hydrogel matrix than larger molecules [34]. The Fickian diffusion model is commonly used to describe the release of small molecules from hydrogels. For larger molecules or macromolecular drugs (e.g., proteins or peptides), the diffusion process is slower due to their larger size and the interactions between the drug and the hydrogel network.

The physical structure of the hydrogel, including its cross-link density and the pore size, significantly influences drug release. A loosely cross-linked hydrogel with larger pores allows for faster diffusion of the drug, while a tightly cross-linked network restricts drug movement and results in slower release [43]. Additionally, the hydration state of the hydrogel can also affect the drug diffusion rate; as the hydrogel absorbs water and swells, the network expands, potentially allowing for easier drug diffusion. The viscosity of the hydrogel solution, as well as the interactions between the polymer chains and the solvent (often water), can affect the diffusion rate [44]. Strong interactions between the drug and polymer chains can slow down the release, while weaker interactions may promote faster diffusion. The solubility of the drug in the surrounding medium also plays a critical role in the

release rate. Drugs that are more soluble in the external environment tend to diffuse faster than poorly soluble drugs [45]. This is particularly important for hydrogels used in oral drug delivery, where the solubility of the drug in the gastrointestinal fluids influences the release rate. Diffusion-controlled release systems are widely used in the development of oral and topical drug delivery systems. For instance, hydrogels designed for the controlled release of painkillers, antibiotics, or anti-inflammatory drugs use this mechanism to ensure the drug is released over an extended period, reducing the need for frequent dosing and improving patient compliance [44].

3.2 Swelling-Controlled Release

Swelling-Controlled Release occurs when the hydrogel absorbs water from the surrounding environment, causing the network to swell. As the hydrogel swells, it expands, creating larger pores that allow the drug to be released into the surrounding medium. This mechanism is particularly useful for sustained-release formulations, where a gradual and controlled release is desired. When the hydrogel comes into contact with an aqueous environment, water penetrates the network, causing the hydrogel to swell [25]. This swelling process disrupts the cross-links between the polymer chains, allowing the drug to diffuse out of the matrix. The drug's release rate is typically governed by the extent of swelling, which depends on several factors such as: The type of polymer used in the hydrogel (e.g., Chitosan, Sodium Alginate, PEG) influences the swelling behavior. Hydrogels made from hydrophilic polymers tend to absorb more water, leading to a higher degree of swelling [1]. The degree of cross-linking in the hydrogel network affects its ability to swell. A lower cross-link density typically allows for more swelling, while a higher density results in reduced swelling and slower release [23]. The pH, temperature, and ionic strength of the surrounding medium can influence the swelling of the hydrogel. For example, certain pH-sensitive hydrogels may swell more in the acidic conditions of the stomach and less in the neutral or alkaline conditions of the intestine [21]. Swelling-controlled release is commonly used in the development of oral drug delivery systems, especially for sustained-release tablets or capsules. This mechanism is also employed in wound dressings, where hydrogels swell to form a moist environment that promotes healing while releasing drugs, such

as antibiotics, to prevent infection [20].

3.3 Stimuli-Responsive Hydrogels

Stimuli-Responsive Hydrogels (also called smart hydrogels) are designed to change their physical or chemical properties in response to external stimuli, such as pH, temperature, ionic strength, or the presence of specific ions or enzymes [46]. These hydrogels provide a dynamic and highly controlled way to release drugs only when certain conditions are met, making them an attractive option for targeted drug delivery and personalized medicine. pH-Responsive Hydrogels undergo swelling or shrinkage in response to changes in pH. For example, hydrogels made from Sodium Alginate or Chitosan can be designed to swell or shrink in the acidic environment of the stomach, allowing drugs to be released in a controlled manner depending on the pH of the target area [29]. This makes pH-responsive hydrogels highly useful for oral drug delivery, especially for drugs that need to be released in specific parts of the gastrointestinal tract. Temperature-responsive hydrogels change their volume and structure in response to temperature fluctuations. For example, Poly(N-isopropylacrylamide) (PNIPAM) hydrogels exhibit a phase transition around body temperature, making them ideal for injectable drug delivery systems where the hydrogel can be injected as a liquid and then form a gel at body temperature to release the drug locally. Ion-Responsive Hydrogels respond to changes in the ionic strength of the surrounding medium. Calcium alginate hydrogels are one example, where the addition of calcium ions causes the hydrogel to form a gel structure, leading to drug encapsulation and controlled release. These hydrogels are often used for topical drug delivery or in formulations that require quick action in response to specific ionic environments. Enzyme-Responsive Hydrogels degrade or swell in response to the presence of specific enzymes [30, 31]. They are useful for targeted drug delivery, where the drug is released in the presence of enzymes found in a specific tissue or organ, such as in cancer therapy where enzymes present in tumor tissues can trigger drug release. Stimuli-responsive hydrogels are particularly promising for smart drug delivery systems. They allow for on-demand drug release, ensuring that drugs are delivered only when needed, which minimizes side effects and improves therapeutic efficacy. For instance, these hydrogels are being explored for cancer therapy, where the drug is released in response to specific pH or enzyme

changes at the tumor site [31].

3.4 Combination Systems

Combination Systems refer to hydrogels that integrate multiple release mechanisms to achieve more controlled and effective drug delivery. These systems combine the advantages of diffusion-controlled release, swelling-controlled release, and stimuli-responsive release to create a tailored drug delivery profile that meets the specific needs of the drug and the patient. In combination systems, two or more release mechanisms work in parallel or sequentially. For example, a hydrogel could release the drug through diffusion initially, followed by a swelling process that further enhances release over time. Alternatively, stimuli-responsive hydrogels could be combined with diffusion-controlled or swelling-controlled systems to provide targeted release in response to specific environmental triggers [26]. Combination systems provide greater flexibility and precision in controlling drug release rates. By targeting specific release profiles, combination systems can enhance the therapeutic efficacy of the drug and reduce side effects. Multi-mechanism systems can deliver drugs to specific tissues or organs, improving localized treatment [26]. Combination systems are particularly useful in complex drug delivery applications, such as in oncology, diabetes management, and wound healing, where multiple release phases or targeted delivery are required. For instance, a combination of pH-sensitive and diffusion-controlled release systems can be used to release a drug specifically in the acidic environment of the stomach and intestines.

4. Applications of Hydrogels in Drug Delivery

Hydrogels have emerged as versatile materials for a wide range of pharmaceutical applications due to their unique properties, such as high water content, biocompatibility, and the ability to encapsulate and release drugs in a controlled and sustained manner. Their ability to be tailored for specific drug release profiles makes them ideal candidates for various drug delivery systems. This section discusses the key applications of hydrogels in oral drug delivery, topical and transdermal drug delivery, injectable hydrogels, ocular drug delivery, and cancer therapy [47].




Figure 1: Applications of hydrogels [46]

4.1 Oral Drug Delivery

Hydrogels have gained significant attention as drug delivery systems for oral administration, particularly for sustained release formulations. When administered orally, the hydrogel undergoes a phase transition or swelling in response to the pH of the gastrointestinal (GI) tract, providing controlled and prolonged drug release. The gel matrix can protect sensitive drugs from gastric acid degradation and deliver them to the intended target site, such as the small intestine or colon, where absorption is more favorable. Hydrogels used in oral drug delivery systems are designed to expand and contract in response to changes in pH or ionic concentration, which helps control the release rate of the drug. pH-sensitive hydrogels, for instance, are particularly useful for targeting specific areas of the GI tract. For example, drugs that are sensitive to the acidic conditions of the stomach can be encapsulated in a pH-sensitive hydrogel, which only begins to release the drug when it reaches a more neutral pH environment, such as in the intestines. In addition to offering sustained release, hydrogels can also provide site-specific delivery. For instance, Sodium

Alginate or Chitosan-based hydrogels are used to target drugs directly to the colon for treating inflammatory bowel diseases (IBD) such as ulcerative colitis [20-22]. The colon-targeted hydrogels release drugs only when they reach the colon, ensuring that therapeutic agents like anti-inflammatory drugs or immunomodulators are delivered precisely where they are needed. The advantage of using hydrogels for oral drug delivery is that they can help reduce the frequency of drug administration, which improves patient compliance, especially for chronic diseases. Hydrogels also increase the bioavailability of poorly water-soluble drugs by encapsulating them in a gel matrix that enhances dissolution and absorption in the gastrointestinal tract [48-51].

4.2 Topical and Transdermal Drug Delivery

Hydrogels are extensively used in topical drug delivery systems, especially for wound healing, burn treatment, and other skin conditions. Hydrogels are able to maintain a moist environment around the wound, which promotes faster healing, reduces scarring, and prevents infection. Their ability to form a protective barrier while delivering drugs such as antibiotics or analgesics makes them ideal for managing wounds, burns, and skin ulcers. Hydrogels for wound healing typically consist of materials like Chitosan, Sodium Alginate, and gelatin. These materials have been shown to support tissue regeneration by allowing controlled release of bioactive agents like growth factors or anti-inflammatory drugs. For example, Chitosan-based hydrogels have demonstrated antimicrobial properties and are used to treat chronic wounds, while Sodium Alginate hydrogels are often used to create moist wound dressings that aid in healing. Hydrogels also show significant promise in transdermal drug delivery, where drugs are delivered through the skin into the bloodstream. This is particularly useful for chronic conditions that require consistent drug delivery, such as hormone replacement therapy (e.g., estradiol patches) or nicotine replacement therapy (e.g., nicotine patches). The advantages of hydrogels in transdermal applications include their flexibility, comfort, and biocompatibility. The ability to release drugs over an extended period of time via transdermal hydrogels ensures a steady plasma concentration of the drug, thereby reducing peaks and troughs in drug levels that can occur with oral administration. Additionally, temperature-sensitive hydrogels are used in transdermal systems,

where the hydrogel undergoes a phase transition at body temperature to form a gel and release the drug [14, 19, 45].

4.3 Injectable Hydrogels

Injectable hydrogels represent one of the most versatile drug delivery systems, especially for localized treatment and long-acting delivery. These hydrogels are designed to be injected into the body in a sol-gel form (i.e., as a liquid that transitions into a gel once injected) and can be used for a variety of medical conditions. One significant advantage of injectable hydrogels is their ability to provide sustained drug release over an extended period of time [14]. Drugs such as antibiotics, anti-inflammatory agents, and chemotherapy drugs can be encapsulated within the gel matrix and delivered over several days or weeks, depending on the cross-linking density and composition of the hydrogel. For example, polymer-based hydrogels such as PEG-based hydrogels are commonly used in injectable formulations due to their biocompatibility and ability to control the release of large-molecule drugs. In cancer therapy, injectable hydrogels can be designed to deliver chemotherapeutic drugs directly to the tumor site. This is particularly important in reducing systemic toxicity and enhancing the therapeutic efficacy of chemotherapy. Hydrogels can be engineered to respond to the unique pH and temperature conditions of tumor tissues, releasing the drug in a controlled manner when the hydrogel comes into contact with the tumor. Injectable hydrogels can also be used for gene therapy, where plasmid DNA or siRNA is encapsulated in the hydrogel and injected at the tumor site for localized release. This method ensures that the therapeutic agent is delivered directly to the tumor cells, thus minimizing the risk of side effects and improving the overall outcome of the treatment [52, 53].

4.4 Ocular Drug Delivery

Hydrogels are also used for ocular drug delivery, offering significant advantages over traditional eye drop formulations. The main challenge with eye drops is that they often wash away quickly due to tear production, leading to poor bioavailability of the drug and requiring frequent administration. Hydrogels, on the other hand, can adhere to the eye's surface and provide sustained release of the drug over an extended period. Hydrogels used for ocular drug delivery typically consist of pH-sensitive materials, such as Sodium Alginate or Carbopol, which can undergo a

transition in response to the pH of the tear fluid. This allows for controlled release of drugs, such as anti-glaucoma agents, antibiotics, or anti-inflammatory drugs, at the site of action. For example, hydrogel contact lenses have been developed to release anti-glaucoma drugs slowly over time, allowing for reduced dosing frequency and improved patient compliance. The ability of hydrogels to be used in ocular inserts or contact lenses offers a promising alternative to traditional eye drop therapies, improving the management of diseases like glaucoma and cataracts [36, 54, 55].

4.5 Cancer Therapy

Hydrogels are increasingly being employed in cancer therapy due to their ability to deliver drugs in a targeted and controlled manner, minimizing the adverse effects typically associated with conventional chemotherapy. One of the key advantages of hydrogels in cancer treatment is their ability to encapsulate both chemotherapeutic drugs and gene-based therapies, providing a controlled release of these agents directly to the tumor site. Hydrogels can be modified to respond to the unique environmental conditions found in tumors, such as the acidic pH, low oxygen levels, and overexpression of certain enzymes [41, 42, 56]. pH-sensitive hydrogels are particularly useful in delivering drugs directly to tumors, as they undergo swelling or degradation in the low pH environment of the tumor microenvironment, releasing the encapsulated drug. Additionally, hydrogels can be functionalized with targeting ligands (such as antibodies or peptides) that specifically bind to receptors overexpressed on tumor cells, allowing for site-specific drug delivery. This targeted approach not only improves the drug's efficacy but also minimizes the systemic toxicity typically associated with chemotherapy. In addition to small molecules, hydrogels are also being explored as delivery systems for gene-based therapies in cancer treatment. DNA, RNA, and siRNA can be encapsulated in hydrogels, allowing for their controlled release at the tumor site. The ability to deliver genes or gene silencers directly to cancer cells opens new possibilities for treating cancers that are resistant to conventional therapies [6, 28, 57].

5. Advantages of Hydrogels in Pharmaceuticals

Hydrogels have gained significant popularity in pharmaceutical applications due to their unique properties, such as high water content, biocompatibility, and versatility in drug delivery. These properties provide numerous benefits over traditional drug

delivery methods. This section discusses the key advantages of hydrogels in pharmaceuticals, including biocompatibility, controlled release profiles, sustained drug delivery, targeted delivery, and ease of fabrication and modification.

5.1 Biocompatibility

Biocompatibility refers to the ability of a material to perform with an appropriate host response in a specific application. Hydrogels are considered highly biocompatible, which means they can interact with living tissues without causing adverse effects such as inflammation, toxicity, or allergic reactions [7, 11, 58, 59]. This is particularly important in pharmaceutical and biomedical applications, where materials are introduced into the body. Hydrogels are typically composed of natural polymers like Chitosan, Sodium Alginate, or Gelatin, or synthetic polymers such as PEG (Polyethylene Glycol). Both types of hydrogels are known for their low immunogenicity, making them suitable for long-term use within the body. The hydrophilic nature of hydrogels, which mimics the natural tissue environment, further enhances their biocompatibility, as the body recognizes and tolerates the water-based structure. Hydrogels can also be engineered to have gradual biodegradability, meaning they break down into non-toxic byproducts, preventing any harmful accumulation of material within the body. This property is especially beneficial for drug delivery systems that require the material to degrade over time as the drug is released, reducing the need for surgical removal and minimizing the risk of local irritation or chronic inflammation [19, 45].

5.2 Controlled Release Profiles

One of the most significant advantages of hydrogels in pharmaceutical applications is their ability to provide controlled release profiles [13, 15, 60-62]. The release rate of the drug from a hydrogel matrix can be precisely controlled, which helps to maintain therapeutic drug levels over extended periods. The diffusion-controlled, swelling-controlled, or stimuli-responsive release mechanisms allow for tailored release, ensuring that the drug is released at a predetermined rate. The precise control over the release rate improves the efficacy of the treatment by maintaining a consistent drug concentration in the bloodstream or at the target site [7, 35, 58]. This is particularly advantageous for chronic diseases or conditions requiring long-term therapy, such as diabetes, cardiovascular diseases, and cancer. Unlike

conventional drug delivery systems, where drug concentrations may fluctuate, hydrogels provide a steady drug release rate, improving the therapeutic outcome and minimizing the risk of under- or overdosing. Moreover, the controlled release offered by hydrogels helps reduce side effects. By preventing peak concentrations that could cause toxicity or adverse reactions, hydrogels ensure that the drug is released in a manner that mimics the body's natural processes, minimizing side effects associated with fluctuating drug levels [51].

5.3 Sustained Drug Delivery

Hydrogels are particularly effective in providing sustained drug delivery, which allows for the continuous release of a drug over an extended period. This feature is beneficial for drugs with a short half-life or those requiring prolonged therapeutic effects. The sustained release of drugs from hydrogels can improve patient compliance by reducing the frequency of drug administration, making it easier for patients to follow their treatment regimen. For example, oral drug delivery systems can benefit from hydrogels that gradually release the drug in the gastrointestinal tract [50]. Injectable hydrogels can also provide sustained release of drugs over several days or weeks, reducing the need for frequent injections, which can be particularly important for chronic conditions like diabetes or cancer. This sustained release mechanism is also crucial in the treatment of diseases requiring long-term therapy or biologic drugs that need to be administered over time. For instance, insulin delivery via hydrogel-based systems can offer continuous and controlled insulin release, mimic the function of a natural pancreas and improving glycemic control in diabetic patients. Furthermore, the low release rate of drugs from hydrogels can minimize the potential for toxicity or side effects, ensuring a safer and more effective treatment [63].

5.4 Targeted Delivery

Hydrogels offer significant advantages in the targeted delivery of drugs, allowing the drugs to be delivered directly to the site of action, minimizing systemic exposure, and reducing off-target effects. This targeted approach is particularly important for the treatment of localized diseases or conditions, such as cancer, inflammatory diseases, and ocular disorders. Targeted delivery is achieved by modifying the hydrogel to respond to the specific pH, temperature, or ionic strength of the target

area. For example, pH-sensitive hydrogels can release their drug payload in response to the acidic pH of the tumor microenvironment, while temperature-sensitive hydrogels can release drugs when injected into the body, where body temperature triggers a gel-to-liquid transition. Stimuli-responsive hydrogels can be designed to release drugs specifically at sites with inflammatory markers or overexpressed receptors [30]. In cancer therapy, hydrogel-based systems can be functionalized with targeting ligands, such as antibodies, that bind specifically to cancer cell receptors, ensuring that the drug is delivered only to the tumor cells and reducing the potential for side effects in healthy tissues. Similarly, hydrogels can be used in gene therapy, where they deliver DNA or RNA molecules specifically to diseased tissues or cells, improving therapeutic outcomes and minimizing systemic toxicity. The ability to target specific tissues or organs also enhances drug stability and efficacy, as the drug is concentrated in the intended site, ensuring that the required dose is delivered precisely where it is needed, and reducing wasteful distribution to other parts of the body [57].

5.5 Ease of Fabrication and Modification

Hydrogels can be easily fabricated and modified to suit specific applications, making them highly adaptable for various drug delivery systems. The wide range of available materials, both natural and synthetic, allows hydrogels to be tailored in terms of mechanical properties, degradation rates, and drug release profiles. For instance, natural hydrogels like Chitosan, Sodium Alginate, and Gelatin can be cross-linked with various agents to control their mechanical strength and swelling behavior. Similarly, synthetic hydrogels such as PEG or PVA can be chemically modified to enhance their biodegradability, drug-loading capacity, or responsiveness to specific stimuli. The modular design of hydrogels allows for the incorporation of bioactive agents such as growth factors, enzymes, or antibiotics [6]. This ability to modify the hydrogel matrix provides the flexibility needed to design multifunctional drug delivery systems, where hydrogels can be used not only to release a drug but also to accelerate healing or promote tissue regeneration, as in wound healing applications. Furthermore, hydrogels can be engineered to have specific release kinetics, such as zero-order release (constant release rate), first-order release (rate decreases over time), or burst release (rapid release followed by sustained release).

This adaptability makes hydrogels suitable for a wide range of pharmaceutical applications, including oral and topical formulations, as well as injectable and ocular drug delivery systems. Hydrogels offer a variety of advantages in pharmaceutical applications, including biocompatibility, the ability to provide controlled release profiles, sustained drug delivery, targeted delivery, and ease of fabrication and modification. These properties make hydrogels ideal for designing drug delivery systems that are both effective and safe, improving patient outcomes and compliance. With continued advancements in hydrogel technology, the potential applications in drug delivery will only continue to expand, providing even more sophisticated solutions to modern pharmaceutical challenges [6].

6. Challenges in Hydrogel Drug Delivery Systems

While hydrogels offer several advantages as drug delivery systems, there are still various challenges that need to be addressed to enhance their effectiveness, scalability, and regulatory acceptance [28]. These challenges include issues related to stability, drug loading efficiency, scalability, regulatory hurdles, and biodegradability. This section discusses each of these challenges in detail and highlights their impact on the development and use of hydrogel-based drug delivery systems.

6.1 Stability Issues

One of the primary challenges in using hydrogels for drug delivery is their stability over time, both in terms of their physical properties and their ability to retain and release drugs consistently. Stability concerns can be categorized into chemical stability, mechanical stability, and drug stability [5]. Over time, hydrogels may undergo chemical degradation, especially when exposed to environmental factors such as heat, light, or oxygen. This degradation can lead to a breakdown of the polymer network, affecting the hydrogel's structural integrity and compromising its drug release profile. For instance, hydrolytic degradation of the polymer matrix can alter the network structure, resulting in uncontrolled drug release [64]. Hydrogels need to maintain their structural integrity during the drug release process, particularly when subjected to swelling or changes in the surrounding environment. Excessive swelling or contraction can cause the hydrogel to lose its mechanical strength, potentially leading to premature drug release or failure to release the drug

as intended. This is particularly problematic in injectable hydrogels, where maintaining the integrity of the gel once it has been injected into the body is crucial for localized drug delivery [25]. The stability of the drug encapsulated within the hydrogel is also a critical concern. Many drugs, particularly biologics such as proteins or peptides, are susceptible to degradation over time due to exposure to water, heat, or other environmental factors. This degradation can reduce the therapeutic efficacy of the drug and, in some cases, cause the formation of toxic byproducts. Therefore, ensuring the stability of both the hydrogel and the drug is essential for the success of these delivery systems. To address these stability concerns, extensive formulation optimization is required. This may include using stabilizing agents or designing hydrogels with improved cross-linking and pH control to maintain stability during storage and use [65].

6.2 Drug Loading Efficiency

Achieving high drug loading efficiency without compromising the structural integrity of the hydrogel is a significant challenge. Drug loading refers to the amount of drug that can be effectively encapsulated within the hydrogel matrix. The drug loading efficiency is crucial because it determines how much therapeutic agent is available for release, and therefore, the overall effectiveness of the drug delivery system. Many hydrogels, especially hydrophilic hydrogels, tend to have difficulty loading hydrophobic drugs. Hydrophilic hydrogels generally have a tendency to solvate and release hydrophilic drugs more efficiently, while hydrophobic drugs are poorly soluble in the gel matrix, making it difficult to achieve high loading efficiency without specialized modifications [66]. In order to improve drug loading efficiency, hydrogels may need to be modified with hydrophobic domains or drug solubilizing agents. Loading large amounts of drug into a hydrogel matrix can compromise its structural integrity. Excessive drug incorporation can interfere with the hydrogel's cross-linking density, leading to a less stable structure and possibly affecting the release rate [67]. High drug loadings can also lead to uneven drug distribution, which may result in unpredictable drug release kinetics. Achieving uniform drug distribution within the hydrogel is another challenge. Uneven loading of the drug can result in burst release, where a large amount of the drug is released rapidly at the start, potentially causing toxic side effects or insufficient therapeutic effect. The

goal is to achieve a homogeneous drug distribution within the hydrogel matrix to enable controlled release over time. Optimizing drug loading efficiency requires balancing the hydrogel's structural properties with the desired drug release profile. Strategies such as multi-step loading processes, surface modification, and composite hydrogels are used to address these challenges [68].

6.3 Scalability

Scaling up the production of hydrogel formulations from the laboratory to commercial production presents several challenges [2]. While hydrogels are relatively simple to fabricate on a small scale, scaling up the process often introduces complications related to uniformity, quality control, and manufacturing costs. One of the key challenges in scaling up the production of hydrogels is ensuring uniformity and consistency in the gel formulation. In a lab setting, it is easier to control the polymer concentration, cross-linking density, and swelling properties of the hydrogel. However, scaling up requires the maintenance of these parameters on a larger scale, which can be difficult to achieve without process optimization [69]. Any inconsistencies in the production process can result in batch-to-batch variability, leading to unpredictable drug release profiles and potentially suboptimal therapeutic outcomes. The cost of producing hydrogels at a commercial scale can be significant. The cost of raw materials, particularly natural polymers like Chitosan and Sodium Alginate, can fluctuate, and the manufacturing processes may require specialized equipment. Scaling up the hydrogel production process may also require investment in automated systems for mixing, cross-linking, and drying, which can further drive up costs. When scaling up for commercial use, hydrogel formulations must meet Good Manufacturing Practices (GMP) standards and regulatory guidelines [70]. This includes sterility requirements, batch consistency, and quality assurance processes to ensure that the final product meets the standards required for clinical use [68].

6.4 Regulatory Hurdles

The regulatory landscape for hydrogel-based drug delivery systems can be complex and varies across different regions. Hydrogel formulations are classified as medical devices, pharmaceuticals, or combination products, depending on their intended use. This classification determines the regulatory requirements that must be met for

approval and market access. The approval process for hydrogel-based drug delivery systems can be lengthy and involves preclinical testing, clinical trials, and manufacturing validation. Regulatory agencies such as the FDA (U.S. Food and Drug Administration), the EMA (European Medicines Agency), and other national health authorities require extensive safety and efficacy data before granting approval for new hydrogel formulations [71]. When hydrogels are used as a drug delivery system (e.g., hydrogel-loaded drugs), they may be considered a combination product, requiring approval as both a drug and a device. This can complicate the approval process, as the product must meet the standards for both drug safety and device performance, including biocompatibility, sterility, and manufacturing consistency. After approval, hydrogel-based products must undergo post-market surveillance to monitor long-term safety and effectiveness. This adds another layer of regulatory oversight, as any issues with stability, drug release, or adverse reactions may require the hydrogel product to be re-evaluated or withdrawn from the market [72].

6.5 Biodegradability

Biodegradability is often viewed as a key advantage of hydrogels, as they break down over time into non-toxic byproducts, reducing the need for surgical removal. However, this property can also present challenges in certain situations. In some cases, hydrogels may degrade too quickly, leading to the early release of the encapsulated drug before it reaches the target site. This premature degradation can compromise the effectiveness of the drug delivery system and potentially cause suboptimal therapeutic outcomes [73]. For instance, if the hydrogel breaks down in the stomach before reaching the intestine, the drug may be released in the wrong area, reducing its absorption. To overcome this challenge, hydrogels need to be designed with controlled degradation rates that match the desired drug release profile. This can be achieved by modifying the polymer structure, adjusting cross-link density, or incorporating biodegradable additives that control the hydrogel's rate of degradation. In some cases, the degradation of hydrogels may result in the accumulation of byproducts within the body, which can lead to toxicity or immune response. While many hydrogels degrade into harmless byproducts, some may produce intermediate products that need to be carefully monitored to prevent unwanted side effects [21].

7. Future Trends and Developments

The field of hydrogel-based drug delivery systems is rapidly evolving, with continuous innovations that promise to revolutionize the way drugs are delivered and administered. The development of smart and responsive hydrogels, hybrid and nanocomposite hydrogels, the use of 3D printing, and the integration of personalized medicine are among the most promising areas of growth. These advancements hold the potential to improve the effectiveness, precision, and patient compliance of drug delivery systems. This section explores the future trends and developments in hydrogel-based drug delivery systems.

7.1 Smart and Responsive Hydrogels

Smart hydrogels, also referred to as stimuli-responsive hydrogels, represent the future of drug delivery due to their ability to respond dynamically to specific environmental stimuli. Unlike traditional hydrogels that release drugs at a constant rate, smart hydrogels can be designed to release drugs only when triggered by particular changes in their surroundings. These hydrogels respond to physical, chemical, or biological stimuli, such as temperature, pH, ionic strength, or the presence of specific enzymes [3]. The future of drug delivery will likely see multi-stimuli responsive hydrogels, which respond to multiple environmental cues. For example, a hydrogel could be designed to respond to both pH changes in the gastrointestinal tract and temperature variations in the body. This ability to react to multiple signals enables a more precise and controlled release of drugs, offering a higher degree of customization. These multi-responsive systems are especially useful for site-specific drug delivery, where the hydrogel releases drugs only in the desired location within the body. Smart hydrogels are particularly attractive for targeted therapy, as they can be engineered to respond to the specific conditions of a disease site, such as tumors, which often have distinct pH, temperature, and enzyme profiles [13]. For example, pH-sensitive hydrogels can be used to deliver drugs specifically to tumors, where the acidic environment triggers the release of the drug. Similarly, hydrogels that respond to temperature changes can be utilized for injectable drug delivery systems, where the hydrogel remains in liquid form for easy injection and transitions into a gel at body temperature to release the drug over time. Research is focusing on improving the design of smart hydrogels by incorporating advanced

nanomaterials and bioactive agents that enhance their responsiveness and functionality. The use of molecular recognition sites, biomarkers, and drug-loaded nanoparticles integrated into hydrogels could further improve their efficiency in controlled drug release [46].

7.2 Hybrid and Nanocomposite Hydrogels

The combination of hydrogels with nanoparticles or other materials has given rise to a new class of hybrid hydrogels and nanocomposite hydrogels. These materials combine the best features of hydrogels and nanomaterials, leading to significant improvements in drug delivery performance. Nanoparticles, such as liposomes, polymeric nanoparticles, gold nanoparticles, and carbon nanotubes, can be incorporated into hydrogels to enhance drug loading capacity, stability, and targeting [3]. The addition of nanoparticles to the hydrogel matrix not only improves the drug loading efficiency but also increases the mechanical strength and stability of the hydrogel, making it more durable during the drug delivery process. Nanoparticles can also serve as carriers for poorly water-soluble drugs, improving their bioavailability and release profile. Nanocomposite hydrogels have the potential to target specific cells or tissues by functionalizing the nanoparticles with targeting ligands, such as antibodies or peptides. For example, lipid-based nanoparticles incorporated into hydrogels can target cancer cells by binding to tumor-specific markers, ensuring that the drug is released directly at the tumor site [17]. This site-specific drug delivery minimizes systemic side effects and improves the therapeutic efficacy of the drug. The incorporation of nanoparticles can also help protect sensitive drugs, such as biologics, from degradation, improving their stability and shelf-life. In addition, the nano-scale properties of the nanoparticles can promote better drug diffusion within the hydrogel, leading to more efficient release [14].

7.3 3D Printing of Hydrogels

3D printing (also known as additive manufacturing) is an emerging technology that allows the creation of customized hydrogel-based drug delivery systems. With 3D printing, it is possible to fabricate hydrogels with complex, patient-specific geometries and precise drug-loading patterns. This ability to customize drug delivery systems has significant implications for personalized medicine and tailored therapies. One of the key advantages of 3D printing is the ability to produce patient-

specific formulations. For instance, 3D printing can create personalized drug delivery devices that fit the specific anatomy of a patient's body, ensuring optimal drug release profiles and localization of the drug [12]. This could be particularly useful in applications like ocular drug delivery, where a precise fit is required for effective treatment. 3D printing allows for the precise control of the drug-loaded hydrogel's release rate. By adjusting the porosity, cross-linking density, and drug encapsulation method, it is possible to design hydrogels that provide zero-order release (constant release rate), burst release, or sustained release depending on the therapeutic needs [6]. 3D printing technology enables the fabrication of multilayered hydrogels, which can be used for sequential drug delivery. Different drugs can be loaded into each layer of the hydrogel, with each layer designed to release its drug at different rates or times. This technology is ideal for delivering combination therapies or drugs that require multi-step release to enhance therapeutic outcomes [12].

7.4 Personalized Medicine

Personalized medicine is an emerging approach that tailors medical treatments to the individual characteristics of each patient. Hydrogels play a crucial role in this concept by enabling the development of customized drug delivery systems that meet the specific needs of individual patients. Personalized medicine can be used to design drug delivery systems based on factors such as genetic profile, disease state, and patient lifestyle. With advancements in hydrogel technology, it is now possible to create patient-specific drug release profiles. For instance, hydrogels could be engineered to release drugs at specific times, based on a patient's circadian rhythms or specific physiological conditions (e.g., diabetic patients). By designing personalized systems, hydrogels can optimize the therapeutic effect while minimizing side effects. Genetic testing and biomarker analysis can be used to design personalized hydrogel drug delivery systems that account for a patient's genetic makeup and specific disease characteristics. For example, hydrogels could be formulated to release drugs in response to specific biomarkers found in the blood, ensuring the drug is released only when the biomarker is present, providing highly specific treatment. Personalized hydrogels can also improve patient compliance by adapting to the patient's unique treatment needs [14]. For example, a hydrogel that

provides sustained release of a drug over a specified period may be particularly beneficial for elderly patients or those with chronic diseases, as it reduces the frequency of administration. Personalized hydrogels are already being explored for cancer therapy, where drug delivery systems can be tailored to the genetic profile of the tumor, ensuring site-specific drug release and enhancing therapeutic efficacy. By modifying the hydrogel matrix to respond to the unique characteristics of a patient's cancer cells, personalized hydrogel-based drug delivery systems could revolutionize cancer treatment [9].

8. Conclusion

8.1 Summary

Hydrogels have emerged as one of the most promising materials in the field of drug delivery systems, offering unique advantages such as biocompatibility, controlled release, sustained drug delivery, and targeted delivery. Throughout this review, This study explored the diverse applications and mechanisms by which hydrogels can enhance pharmaceutical formulations, making them highly versatile platforms for delivering a wide range of therapeutic agents. This study discussed the various types of hydrogels, including natural hydrogels like Chitosan and Sodium Alginate, as well as synthetic hydrogels like PEG and PVA, and their use in drug delivery. These hydrogels offer unique properties such as biodegradability, pH-sensitivity, and the ability to encapsulate both hydrophilic and hydrophobic drugs, ensuring their utility in a wide array of applications, from oral drug delivery to topical therapies. The mechanisms of drug release in hydrogels were examined, with particular attention given to diffusion-controlled release, swelling-controlled release, and stimuli-responsive release systems. These mechanisms allow for tailored drug delivery, ensuring that drugs are released at the desired rate and site, which minimizes side effects and improves therapeutic outcomes. Additionally, the applications of hydrogels in oral, topical, injectable, ocular, and cancer therapies were discussed, highlighting their potential to revolutionize drug delivery in various therapeutic areas. Hydrogels' ability to deliver drugs in a controlled and targeted manner opens new avenues for the treatment of chronic diseases, localized conditions, and cancer, offering significant improvements in patient compliance and drug efficacy. The advantages of hydrogels, including their biocompatibility, ability

to provide controlled and sustained release, and ease of modification, were emphasized as key factors contributing to their growing use in drug delivery systems. However, challenges such as stability, drug loading efficiency, scalability, regulatory hurdles, and biodegradability remain areas for ongoing research and improvement.

8.2 Future Prospects

The field of hydrogel-based drug delivery systems is still in the early stages of its potential, with ongoing research exploring ways to overcome current challenges and improve the efficacy of these systems. Smart and responsive hydrogels are at the forefront of this research, with promising developments in multi-stimuli responsive systems that can release drugs in response to pH, temperature, or enzymes. These systems will allow for more precise control over drug release, making them ideal for targeted therapy in conditions such as cancer and inflammatory diseases. The integration of hydrogels with nanoparticles and nanocomposites is another exciting area of development. The combination of hydrogels with nanoparticles has the potential to enhance drug loading capacity, improve stability, and enable targeted drug delivery. 3D printing technology also holds promise in creating customized hydrogel drug delivery systems, tailored to individual patient needs. This will allow for the fabrication of drug delivery devices with precise geometries, drug-release patterns, and multi-drug delivery capabilities, which can significantly improve therapeutic outcomes. Furthermore, personalized medicine is expected to play a central role in the future of hydrogel-based drug delivery systems. With advancements in genomics and biomarker analysis, hydrogels can be engineered to deliver drugs based on a patient's genetic profile, disease state, and response to treatment. Personalized drug delivery systems can provide tailored therapies, improving drug efficacy and minimizing side effects. As research in this area continues to evolve, This study expect to see hydrogels playing an increasingly significant role in biologics delivery, gene therapy, vaccines, and regenerative medicine. The ability to design hydrogels that release drugs in response to specific biomarkers or disease conditions will open new frontiers in precision medicine and targeted treatment.

8.3 Final Thoughts

The outlook for hydrogels in drug delivery is incredibly promising. With advancements in smart hydrogels, nanocomposite systems, 3D printing, and personalized medicine, hydrogels are poised to become a cornerstone in the development of advanced drug delivery systems. They offer unparalleled advantages in terms of controlled release, sustained drug delivery, and targeted treatment, making them an ideal solution for chronic diseases, cancer, and other conditions that require precision and long-term management. Despite the challenges that remain, such as improving scalability and addressing regulatory concerns, the ongoing research in hydrogel-based drug delivery systems is likely to lead to innovative solutions that will overcome these barriers. As new technologies and materials are developed, This study expect hydrogels to become an essential tool in the arsenal of modern pharmaceuticals, revolutionizing how drugs are delivered and improving patient outcomes across a wide range of therapeutic areas. Hydrogels' ability to respond to multiple stimuli, target specific sites, and release drugs in a controlled manner makes them an indispensable part of the future of drug delivery. With continued innovation, personalized therapies and smarter drug delivery systems will be the norm, offering tailored treatment options that are both effective and safe, ultimately transforming the landscape of modern medicine.

References

- [1] B. Cheng, B. Pei, Z. Wang, and Q. Hu, "Advances in chitosan-based superabsorbent hydrogels," *Rsc Advances*, vol. 7, no. 67, pp. 42036-42046, 2017.
- [2] E. L. Krasnopeevea, G. G. Panova, and A. V. Yakimansky, "Agricultural applications of superabsorbent polymer hydrogels," *International Journal of Molecular Sciences*, vol. 23, no. 23, p. 15134, 2022.
- [3] Y. Liu, J. Liu, A. Zhang, G. Zhao, B. Jiang, and X. Zhao, "Application prospect of Marine polysaccharide hydrogels in promoting wound healing: A Review," *Carbohydrate Research*, p. 109673, 2025.
- [4] A. Berradi, F. Aziz, M. E. Achaby, N. Ouazzani, and L. Mandi, "A comprehensive review of polysaccharide-based hydrogels as promising

- biomaterials," *Polymers*, vol. 15, no. 13, p. 2908, 2023.
- [5] J. Yang, Y. Chen, L. Zhao, J. Zhang, and H. Luo, "Constructions and properties of physically cross-linked hydrogels based on natural polymers," *Polymer Reviews*, vol. 63, no. 3, pp. 574-612, 2023.
- [6] S. S. Shah, B. Ramos, L. Otubo, and A. C. S. C. Teixeira, "Deep Removal and Photodegradation of Methylene Blue Dye Using Superabsorbent Polymer Hydrogel Composite with Activated Charcoal and TiO₂ Nanoparticles," *ACS Omega*, 2025.
- [7] W. Zhang *et al.*, "Factors affecting the properties of superabsorbent polymer hydrogels and methods to improve their performance: a review," *Journal of Materials Science*, vol. 56, no. 29, pp. 16223-16242, 2021.
- [8] Z. Li *et al.*, "Global Research and Emerging Trend of Superabsorbent Hydrogel Applied to Agriculture Based on Visual Analysis," *Water, Air, & Soil Pollution*, vol. 236, no. 6, p. 359, 2025.
- [9] M. Z. Hassan, "Types of wounds and their causes," *Hydrogels for Wound Healing*, pp. 21-28, 2026.
- [10] R. Asmat *et al.*, "Graphene oxide-reinforced chitosan/polyethylene glycol/poly (acrylic acid) ternary blend hydrogels: A promising material for biomedical applications," *Environmental Technology & Innovation*, p. 104430, 2025.
- [11] S. Ismaeilimoghadam, B. Azimi, M. Jonoobi, and S. Danti, "Highly Performing Polysaccharide Hydrogels can Replace Acrylic Acid-Based Superabsorbent Polymers in Sanitary Napkins," *Macromolecular Materials and Engineering*, vol. 310, no. 3, p. 2400278, 2025.
- [12] A. Khademi, A. Khandan, and P. Iranmanesh, "Hydrogels for dental pulp repair: enhancing physicochemical and regenerative potential with CaP-loaded alginate-gelatin hydrogel scaffolds: a FEM and ANN modeling," *Nanomedicine Journal*, 2025.
- [13] A. Hajalilou, "Liquid Metal–Polymer Hydrogel Composites for Sustainable Electronics: A Review," *Molecules*, vol. 30, no. 4, p. 905, 2025.
- [14] A. F. Chamorro, M. Palencia, and E. M. Combatt, "Starch Hydrogels for

- Slow and Controlled-Release Fertilizers: A Review," *Polymers*, vol. 17, no. 8, p. 1117, 2025.
- [15] R. Michalik and I. Wandzik, "A mini-review on chitosan-based hydrogels with potential for sustainable agricultural applications," *Polymers*, vol. 12, no. 10, p. 2425, 2020.
- [16] O. Ramírez, S. Castillo, S. Bonardd, C. Saldías, D. Díaz Díaz, and A. Leiva, "Poly (ionic liquid)-Based Hydrogel for Emerging Pollutant Removal and Controlled Drug Delivery," *ACS Applied Polymer Materials*, vol. 6, no. 22, pp. 13865-13876, 2024.
- [17] L. Zhao, Y. Zhou, J. Zhang, H. Liang, X. Chen, and H. Tan, "Natural polymer-based hydrogels: From polymer to biomedical applications," *Pharmaceutics*, vol. 15, no. 10, p. 2514, 2023.
- [18] M. Abazari *et al.*, "Polysaccharide-based hydrogels containing herbal extracts for wound healing applications," *Carbohydrate polymers*, vol. 294, p. 119808, 2022.
- [19] M. Muhammad, M. Tawfic, M. Taha, and A. Elsabbagh, "Review of design and manufacturing of superabsorbent polymers (SAPs) hydrogel for agriculture in arid areas," *Discover Materials*, vol. 4, no. 1, p. 43, 2024.
- [20] S. Salehi, H. Ghomi, S. Hassanzadeh-Tabrizi, N. Koupaei, and M. Khodaei, "Antibacterial and osteogenic properties of chitosan-polyethylene glycol nanofibre-coated 3D printed scaffold with vancomycin and insulin-like growth factor-1 release for bone repair," *International Journal of Biological Macromolecules*, vol. 298, p. 139883, 2025.
- [21] S. Ahmad Dar and F. M. Abd Al Galil, "Biodegradation, biosynthesis, isolation, and applications of chitin and chitosan," in *Handbook of biodegradable materials*: Springer, 2022, pp. 1-42.
- [22] C. O. Dimkpa, C. Deng, Y. Wang, I. O. Adisa, J. Zhou, and J. C. White, "Chitosan and zinc oxide nanoparticle-enhanced tripolyphosphate modulate phosphorus leaching in soil," *ACS Agricultural Science & Technology*, vol. 3, no. 6, pp. 487-498, 2023.
- [23] Medha and S. Sethi, "Chitosan based hybrid superabsorbent for controlled

- drug delivery application," *Biotechnology Progress*, vol. 40, no. 2, p. e3418, 2024.
- [24] F. Mustapa *et al.*, "Development of Cellulose Acetate-Polyethylene Glycol-Chitosan Membrane-Embedded TiO₂ Nanoparticles for Reverse Osmosis Desalination," *Water, Air, & Soil Pollution*, vol. 236, no. 1, p. 61, 2025.
- [25] P. A. Mistry, M. N. Konar, S. Latha, U. Chadha, P. Bhardwaj, and T. K. Eticha, "Chitosan superabsorbent biopolymers in sanitary and hygiene applications," *International Journal of Polymer Science*, vol. 2023, no. 1, p. 4717905, 2023.
- [26] M. Nawaz *et al.*, "Synthesis of Titanium Dioxide-Embedded Alginate-Chitosan-Based Coating for Enhanced Wheat Seed Germination under Abiotic Stress," *ChemistrySelect*, vol. 10, no. 33, p. e02002, 2025.
- [27] J. Zhang, S. Bai, S. Zhao, and X. Guan, "Synthesis of a chitosan-based superabsorbent polymer and its influence on cement paste," *International Journal of Biological Macromolecules*, vol. 282, p. 136676, 2024.
- [28] Y. Chen and H.-m. Tan, "Crosslinked carboxymethylchitosan-g-poly (acrylic acid) copolymer as a novel superabsorbent polymer," *Carbohydrate Research*, vol. 341, no. 7, pp. 887-896, 2006.
- [29] P. Tordi, F. Ridi, P. Samorì, and M. Bonini, "Cation-alginate complexes and their hydrogels: A powerful toolkit for the development of next-generation sustainable functional materials," *Advanced Functional Materials*, vol. 35, no. 9, p. 2416390, 2025.
- [30] S. Ismaeilimoghadam *et al.*, "Development and characterization of sodium alginate-based bio-hybrid super absorbent polymer with high retention capacity suitable for baby diapers," *Journal of Polymers and the Environment*, vol. 32, no. 10, pp. 5212-5230, 2024.
- [31] K. Naseem, M. H. Tahir, F. Farooqi, S. Manzoor, and S. U. Khan, "Strategies adopted for the preparation of sodium alginate-based nanocomposites and their role as catalytic, antibacterial, and antifungal agents," *Reviews in Chemical Engineering*, vol. 39, no. 8, pp. 1359-1391, 2023.
- [32] N. Vakili, A. Asefnejad, M. Mohammadi, H. Rezaei, and A. Khandan,

- "Improving physicochemical, mechanical, and biological properties of a porous polyvinyl alcohol/chitosan matrix via modification with magnesium and silicon agents," *Nanomedicine Journal*, vol. 12, no. 3, 2025.
- [33] A. Raees, S. Mir, N. S. Awwad, and H. A. Ibrahim, "Eco-friendly clay reinforced chitosan and polyethylene glycol based nanocomposites for targeted dye removal in wastewater treatment," *International Journal of Biological Macromolecules*, p. 146475, 2025.
- [34] W. Lei *et al.*, "Edible polyethylene glycol modified chitosan nanoparticles: Separation and controlled release of tea polyphenols from multiphasic systems," *International Journal of Biological Macromolecules*, p. 144375, 2025.
- [35] H. Shruthi, K. Puneeth, and G. P. ME, "Experimental Study on Effects of Super Absorbent Polymer (SAP) and Polyethylene Glycol (PEG) as Curing Agents in Concrete," *Grenze International Journal of Engineering & Technology (GIJET)*, vol. 10, 2024.
- [36] M. Nawaz, M. Saeed, M. Zahoor, S. Bibi, and S. Khan, "Synthesis of chitosan-polyethylene glycol-based superabsorbent for enhanced water retention in agriculture," *Journal of Polymer Research*, vol. 32, no. 8, pp. 1-16, 2025.
- [37] S. Selçuk Pekdemir *et al.*, "Nature-derived otolith loaded polyethylene glycol-polycaprolactone electrospun composite nanofiber membranes: preparation, characterization, and biocompatibility evaluation," *Iranian Polymer Journal*, pp. 1-14, 2025.
- [38] P. Jaishankar, S. Kanchidurai, V. SS, C. Venkatasubramanian, and D. Muthu, "Performance of Self Curing Concrete with addition of Polyethylene Glycol 400 and Super Absorbent Polymer," in *E3S Web of Conferences*, 2024, vol. 559, p. 04017: EDP Sciences.
- [39] S. S. El-Khiyami, H. Ali, A. Ismail, and R. Hafez, "Tunable physical properties and dye removal application of novel Chitosan Polyethylene glycol and polypyrrole/carbon black films," *Scientific Reports*, vol. 15, no. 1, p. 20124, 2025.
- [40] R. A. Lusiana, R. Nuryanto, D. Dayanti, N. Muna, T. Safitri, and N. A. Sasongko, "Role of Polyvinyl Alcohol in Enhancing Chitosan Membranes for

Online ISSN

3007-3197

Print ISSN

3007-3189

<http://amresearchreview.com/index.php/Journal/about>

- Desalination: An Experimental and Theoretical Study," *ChemistrySelect*, vol. 10, no. 22, p. e01611, 2025.
- [41] S. Bibi, A. Jamil, T. Yasin, M. A. Rafiq, M. Nawaz, and G. J. Price, "Ultrasound promoted synthesis and properties of chitosan nanocomposites containing carbon nanotubes and silver nanoparticles," *European Polymer Journal*, vol. 105, pp. 297-303, 2018.
- [42] J. Lyu, S. Feng, J. Chen, D. Kong, and R. Song, "The water absorption and release performance and mechanism of superabsorbent polymers in the solution and paste," *Case Studies in Construction Materials*, p. e04955, 2025.
- [43] Z. W. Loh, M. H. M. Zaid, K. A. Matori, M. Z. A. Khiri, W. M. Cheong, and P. Y. Foong, "Mechanical, Fluoride Release, and Antibacterial Performance of Waste-derived Glass Ionomer Cements," *Journal of Materials Research and Technology*, 2025.
- [44] M. Jan, A. H. Shalla, and K. Majid, "Next-Generation Fertilizers: A TiO₂-Chitosan Composite Superabsorbent as a Sustained Release N-Fertilizer," *Langmuir*, vol. 41, no. 9, pp. 6323-6334, 2025.
- [45] X. Qin, Y. Lin, J. Mao, X. Sun, Z. Xie, and Q. Huang, "Research of water absorption and release mechanism of superabsorbent polymer in cement paste," *Polymers*, vol. 15, no. 14, p. 3062, 2023.
- [46] Z. Li, Y. Zhou, T. Li, J. Zhang, and H. Tian, "Stimuli-responsive hydrogels: fabrication and biomedical applications," *View*, vol. 3, no. 2, p. 20200112, 2022.
- [47] J. Reinoza *et al.*, "Fabrication of pullulan-chitosan fiber membranes for enhanced hemostatic applications," *International Journal of Biological Macromolecules*, vol. 308, p. 142552, 2025.
- [48] O. Moradi, A. Hosseini Naeini, M. Kalaei, and S. Mirkhan, "The effect of sustainable applications of chitin and Chitosan to remove Dyed pollutants using adsorption: A review," *Nano*, vol. 18, no. 14, p. 2330006, 2023.
- [49] N. R. Azeez, S. S. Salih, M. Kadhom, H. N. Mohammed, and T. K. Ghosh, "Enhanced termination of zinc and cadmium ions from wastewater employing plain and chitosan-modified mxenes: Synthesis, characterization,

- and adsorption performance," *Green Chemical Engineering*, vol. 5, no. 3, pp. 339-347, 2024.
- [50] N. N. Che Aziz, N. H. Mat Yasin, F. Adam, and S. R. Esa, "Enhancing Biopolymer Composite Films: Molecular Interaction and Functional Properties of Chitosan and *Chlorella vulgaris* Blends for Sustainable Packaging," *Journal of Polymers and the Environment*, pp. 1-19, 2025.
- [51] M. Said, Y. Atassi, M. Tally, and H. Khatib, "Environmentally friendly chitosan-g-poly (acrylic acid-co-acrylamide)/ground basalt superabsorbent composite for agricultural applications," *Journal of Polymers and the Environment*, vol. 26, pp. 3937-3948, 2018.
- [52] B. Batara *et al.*, "Recent Advances, Applications, and Challenges in Superabsorbent Polymers to Support Water Sustainability," *Journal of Applied Polymer Science*, vol. 142, no. 11, p. e56588, 2025.
- [53] Y. Yang *et al.*, "Research advances in superabsorbent polymers," *Polymers*, vol. 16, no. 4, p. 501, 2024.
- [54] M. Nawaz *et al.*, "Synthesis of Polyvinylidene Fluoride/Polyvinyl Chloride/Silver Oxide-Based Nanocomposite Membranes and Evaluation for Its Application in Dialysis," *Polymers for Advanced Technologies*, vol. 36, no. 5, p. e70216, 2025.
- [55] S. Fang *et al.*, "Synthesis of superabsorbent polymers based on chitosan derivative graft acrylic acid-co-acrylamide and its property testing," *International journal of biological macromolecules*, vol. 132, pp. 575-584, 2019.
- [56] V. Losetty *et al.*, "Transformative applications of Polymer-Based metal oxide nanocomposites in medicine, industry, and environmental remediation: A review," *Journal of Inorganic and Organometallic Polymers and Materials*, pp. 1-33, 2025.
- [57] M. Muhammad, M. Tawfic, M. Taha, and A. Elsabbagh, "Design and manufacturing of superabsorbent polymers (SAPs) for agriculture in arid areas," *Scientific Reports*, vol. 15, no. 1, p. 16186, 2025.
- [58] T. T. H. Pham *et al.*, "Frontal polymerization—a rapid route for synthesizing superabsorbent polymers based on jackfruit seed starch grafted acrylic

- monomers," *Materials Research Express*, vol. 12, no. 3, p. 035303, 2025.
- [59] A. Abdolmaleki *et al.*, "Impact of Super Absorbent Polymers (SAPs) on the Morphological, Physiological, and Biochemical Responses of Rapeseed and Maize Under Drought Stress," *Crop Breeding, Genetics and Genomics*, vol. 7, no. 3, 2025.
- [60] Y. Tan, X. Lu, R. He, H. Chen, and Z. Wang, "Influence of superabsorbent polymers (SAPs) type and particle size on the performance of surrounding cement-based materials," *Construction and Building Materials*, vol. 270, p. 121442, 2021.
- [61] Y. Bachra, F. Damiri, M. Berrada, J. Tuteja, and A. Sand, "Introduction of superabsorbent polymers," in *Properties and Applications of Superabsorbent Polymers: Smart Applications with Smart Polymers*: Springer, 2023, pp. 1-18.
- [62] H. Omidian, S. Hashemi, P. Sammes, and I. Meldrum, "Modified acrylic-based superabsorbent polymers. Effect of temperature and initiator concentration," *Polymer*, vol. 39, no. 15, pp. 3459-3466, 1998.
- [63] X. Ma and G. Wen, "Development history and synthesis of super-absorbent polymers: a review," *Journal of Polymer Research*, vol. 27, no. 6, p. 136, 2020.
- [64] S. S. Salih, M. Kadhom, M. A. Shihab, and T. K. Ghosh, "Competitive adsorption of Pb (II) and phenol onto modified chitosan/vermiculite adsorbents," *Journal of Polymers and the Environment*, vol. 30, no. 10, pp. 4238-4251, 2022.
- [65] R. Pattanayak and T. Jena, "Bio-based superabsorbent polymer: Current trends, applications and future scope," in *Bio-based Superabsorbents: Recent Trends, Types, Applications and Recycling*: Springer, 2023, pp. 185-197.
- [66] V. Mechtcherine *et al.*, "Application of super absorbent polymers (SAP) in concrete construction—update of RILEM state-of-the-art report," *Materials and structures*, vol. 54, no. 2, p. 80, 2021.
- [67] Y. Wang *et al.*, "An Artemisia Sphaerocephala Krash gum/acrylic acid-based novel eco-friendly superabsorbent polymer: Its synthesis and properties promoting seed germination," *Journal of Environmental Chemical Engineering*, vol. 12, no. 6, p. 114723, 2024.

Online ISSN

3007-3197

Print ISSN

3007-3189

<http://amresearchreview.com/index.php/Journal/about>

- [68] X. Bian *et al.*, "Antibacterial Materials Based on Natural Superabsorbent Polymer and Their Applications," *Journal of Applied Polymer Science*, p. e57510, 2025.
- [69] F. Shafiq, A. Mahmood, and M. Iqbal, "Agricultural Use of Various Polymeric Nanocomposites and Future Avenues," in *Specialty Polymers and Materials*: Apple Academic Press, 2025, pp. 21-52.
- [70] B. Dadfar, B. Alemdag, and G. Kabay, "The Alchemist, the Scientist, and the Robot: Exploring the Potential of Human-AI Symbiosis in Self-Driving Polymer Laboratories," *Macromolecular Rapid Communications*, p. e00380, 2025.
- [71] N. Bansal *et al.*, "Pyrazole in drug development: a medicinal-chemistry based analysis of USFDA-approved drugs in last decade," *Molecular Diversity*, pp. 1-24, 2025.
- [72] M. Adil *et al.*, "Zinc oxide nanoparticles improved chlorophyll contents, physical parameters, and wheat yield under salt stress," *Frontiers in plant science*, vol. 13, p. 932861, 2022.
- [73] D. Gao, H. Wu, B. Lyu, X. Lu, and J. Ma, "Biodegradable agricultural film based on bone gelatin and PDMS-NH₂: Evaluation of mechanical properties and hydrophobicity," *International Journal of Biological Macromolecules*, vol. 284, p. 138165, 2025.