

Metal-Organic Frameworks (MOFs) for Advanced Solutions in Water Purification, Energy Storage, and Environmental Remediation: A Review

Hassan Saleemi

MSc. University of Punjab, Institute of Chemical Engg & Technology, I.C.E.T Lahore-54590, Pakistan. saleemih72@gmail.com

Samreen Khan

M.Phil. Department of Chemistry, Hazara University, Mansehra-21300, Pakistan. samreenswatikhan9@gmail.com

Sidra Sultana

PhD. Department of Chemistry, Hazara University, Mansehra-21300, Pakistan. syedasidra06091998@gmail.com

Muhammad Adil

M.Phil. Department of Chemistry, Hazara University, Mansehra-21300, Pakistan. adilawan54321@gmail.com

Farzand khan

M.Phil. Department of Chemistry, Hazara University, Mansehra-21300, Pakistan. farzandkhan95@gmail.com

Abdul Moiz

BS (Hons). Department of Earth and Environmental Science, Hazara University, Mansehra-21300, Pakistan. abdulmoizkhanxswati@gmail.com

Masab Saeed

PhD. Department of Chemistry, Hazara University, Mansehra-21300, Pakistan. masabsaeed@hu.edu.pk

Muhammad Tariq Asif

M.Phil. Department of Chemistry, Hazara University, Mansehra-21300, Pakistan. muhammadtariqasif@gmail.com

ABSTRACT

Metal-Organic Frameworks (MOFs) are a class of highly porous materials composed of metal ions or clusters coordinated to organic ligands, forming a three-dimensional network. These materials are distinguished by their high surface area, tunable porosity, and chemical versatility, making them ideal candidates for various applications, particularly in the fields of water purification, energy storage, and environmental remediation. In water purification, MOFs have demonstrated excellent potential in adsorbing heavy metals, organic pollutants, and salts from contaminated water. In energy storage, they have been explored for enhancing the performance of lithium-ion batteries, sodium-ion batteries, supercapacitors, and hydrogen storage systems. Moreover, MOFs play a crucial role in environmental

remediation by capturing harmful gases such as CO₂, NO_x, and SO_x, as well as degrading organic pollutants through photocatalytic processes. This paper provides a comprehensive review of the latest advancements in MOF-based technologies in these areas. The methodology includes an extensive literature review, analysis of key case studies, and discussion of the challenges and future directions for the development and commercialization of MOF-based solutions.

Keywords: Metal-Organic Frameworks, water purification, energy storage, environmental remediation, gas capture.




Figure 1: Schematic Abstract

1. Introduction

Metal-Organic Frameworks (MOFs) are a class of materials composed of metal ions or clusters coordinated to organic ligands to form a three-dimensional structure. These materials exhibit highly porous structures, making them ideal candidates for a variety of applications, particularly in the areas of water purification, energy storage, and environmental remediation. The unique features of MOFs, such as their high surface area, tunable porosity, and chemical stability, allow for their use in a broad spectrum of industrial and environmental processes. In recent years, they have garnered significant attention due to their versatility and potential to address some of the world's most pressing challenges, including the need for efficient

environmental protection and sustainable energy systems. The structure of MOFs is primarily characterized by their extended, crystalline lattices, which are formed through the coordination of metal ions or clusters with organic linkers. This framework can be modified by altering the metal centers, the organic linkers, or both, allowing for a broad range of variations in their structural properties. These modifications allow MOFs to achieve a variety of desired characteristics, such as specific pore sizes, surface areas, and functional groups, which can be tailored for particular applications (Furukawa et al., 2010). For instance, by adjusting the geometry of the organic linkers or the metal centers, the framework's stability, flexibility, and porosity can be fine-tuned, which significantly influences the material's performance in various applications (Zhang et al., 2014). Furthermore, the ease with which these materials can be synthesized under mild conditions using readily available precursors has contributed to their widespread study and use (Kreno et al., 2012).

The significance of MOFs in material science cannot be overstated. Their unique combination of properties—high porosity, high surface area, and a high degree of chemical tunability—has led to their recognition as one of the most promising classes of materials for applications such as gas storage, catalysis, and sensing (Li et al., 2009; Yaghi et al., 2003). These properties arise from the flexibility of MOF structures, which can change in response to external conditions such as temperature, pressure, and chemical environment. This adaptability makes them suitable for a range of applications where other materials might fail. For example, MOFs have been shown to excel in selective gas adsorption, with potential uses in carbon capture and hydrogen storage, as well as in catalysis, where they serve as active sites for a variety of reactions (Furukawa et al., 2010). Moreover, the ease with which MOFs can be functionalized by modifying their metal nodes or organic linkers has further expanded their range of applications, including in fields like drug delivery, water treatment, and environmental monitoring (Dinca et al., 2006). One of the most crucial and growing areas where MOFs have been applied is in the fields of water purification, energy storage, and environmental remediation. Water purification is an urgent global challenge, particularly in areas suffering from water scarcity and contamination. Traditional water treatment methods, such as reverse

osmosis and activated carbon filtration, are often inefficient and expensive, especially when it comes to removing specific pollutants like heavy metals, organic toxins, or salts. MOFs, due to their high surface area and tunable pore sizes, provide an efficient and cost-effective alternative for water purification, capable of adsorbing and removing a wide range of contaminants (Alsaiee et al., 2016). This has led to the development of MOF-based filters and adsorbents that can be employed for both drinking water purification and wastewater treatment (Yang et al., 2017). Similarly, the removal of salt from seawater through desalination remains a challenge, with MOFs being investigated as potential materials for enhancing desalination processes by facilitating the selective separation of ions (Zhou et al., 2015).

MOFs have also made significant strides in energy storage technologies. Energy storage is a critical component in addressing the growing global energy demand and enabling the transition to sustainable energy systems. Batteries, supercapacitors, and hydrogen storage systems are some of the most widely studied energy storage technologies, and MOFs have emerged as key materials for improving the performance of these systems. For example, MOFs can enhance the energy storage capacity of lithium-ion and sodium-ion batteries by improving the conductivity of the electrodes and enhancing the ionic transport (Bachman et al., 2016). Furthermore, MOFs have shown promise in hydrogen storage, with their high surface area and tunable porosity allowing them to store large amounts of hydrogen gas at lower pressures and temperatures, making them an attractive alternative to conventional storage methods (Yoon et al., 2018). Their application in supercapacitors also shows promise, particularly in enhancing the efficiency of charge and discharge cycles, as well as improving the overall lifespan of energy storage systems (Long et al., 2016). In environmental remediation, MOFs have been explored for their ability to capture and sequester harmful pollutants, including volatile organic compounds (VOCs), heavy metals, and greenhouse gases. Environmental contamination, particularly the release of CO₂ and other pollutants into the atmosphere, is a pressing concern due to its contribution to climate change and air pollution. MOFs, due to their high adsorption capacity and selective adsorption properties, offer a promising solution for capturing CO₂ and other pollutants from the air and water (Sumida et al., 2012). Moreover, MOFs have been

employed in the degradation of toxic chemicals, such as pesticides and pharmaceuticals, through photocatalytic or catalytic processes, which further expands their potential applications in environmental protection (Kong et al., 2018). The unique ability of MOFs to selectively target pollutants and their high capacity for adsorption make them an excellent choice for developing sustainable solutions for environmental remediation.

The purpose of this review is to provide a comprehensive overview of the current state of research on MOFs and their applications in water purification, energy storage, and environmental remediation. The scope of this review will encompass the latest advancements in MOF synthesis, structural design, and functionalization, as well as their effectiveness in addressing challenges related to water purification, energy storage, and environmental remediation. Additionally, this review will explore the potential future directions of MOF-based technologies, including the challenges that need to be overcome to facilitate their commercial deployment and real-world applications. By examining the state of the art in these fields, this review aims to highlight the significant contributions that MOFs can make in advancing sustainability and environmental protection, while also addressing key global challenges related to energy storage and water purification.

2. Metal-Organic Frameworks (MOFs): Structure and Properties

Metal-Organic Frameworks (MOFs) are a class of crystalline materials that consist of metal ions or metal clusters coordinated to organic ligands. These materials possess a unique combination of properties, which include tunable porosity, high surface area, and chemical stability. MOFs are known for their exceptional structural flexibility, which allows them to be tailored for specific applications, such as gas storage, catalysis, water purification, and environmental remediation. In this section, we will discuss the basic structure of MOFs, the different types of MOFs, their unique properties, synthesis methods, and functionalization strategies to enhance their performance.

2.1 Basic Structure of MOFs

The fundamental structure of MOFs is based on metal nodes, which are metal ions or clusters, and organic linkers that connect these metal nodes, forming a three-dimensional network. The metal nodes can be single metal ions, such as zinc (Zn),

copper (Cu), or iron (Fe), or metal clusters, which are groups of metal ions coordinated together. The organic linkers are typically organic molecules that contain functional groups capable of coordinating with the metal nodes, such as carboxylates, phosphonates, or pyrazoles (Furukawa et al., 2010). The metal ions and organic ligands together form a crystalline structure that is highly porous, with well-defined cavities that can be used for a variety of applications.

The connectivity between the metal nodes and the organic linkers can be adjusted to control the size and shape of the pores in the material. This structural tunability allows MOFs to be designed with specific pore sizes, surface areas, and chemical environments. These characteristics make MOFs suitable for applications such as gas storage, catalysis, and separation processes (Yaghi et al., 2003). Additionally, the frameworks can exhibit high thermal and chemical stability, which enhances their performance in real-world applications (Li et al., 2019).




Figure 2: *Basic Structure of MOFs*

2.2 Types of MOFs

MOFs can be classified into three main categories based on the size of their pores: porous, microporous, and mesoporous.

2.2.1 Porous MOFs: These are MOFs with large pores, typically greater than 2 nm in diameter. These frameworks can accommodate larger molecules and are often used for applications such as gas storage, drug delivery, and catalysis. The large pores in porous MOFs allow for the incorporation of guest molecules or ions,

making them useful for applications that require high adsorption capacity (Zhou et al., 2015).

2.2.2 Microporous MOFs: Microporous MOFs have pores that are less than 2 nm in diameter. The small pore size of these MOFs gives them a high surface area, which is beneficial for applications such as gas adsorption, separations, and catalysis. Microporous MOFs are typically used in processes that require selective adsorption or separation of small molecules, such as carbon dioxide capture and hydrogen storage (Sumida et al., 2012).

2.2.3 Mesoporous MOFs: Mesoporous MOFs have pores between 2 and 50 nm in diameter. These MOFs have a higher surface area than non-porous materials but are less rigid than microporous MOFs. They are used in applications that require a balance between adsorption capacity and accessibility of the guest molecules, such as in environmental remediation and energy storage (Furukawa et al., 2010). Each type of MOF offers different advantages and can be selected based on the specific requirements of the application. For example, microporous MOFs are ideal for applications requiring high surface area and selective adsorption, whereas mesoporous MOFs may be preferred for applications requiring greater accessibility for larger molecules.

2.3 Unique Properties of MOFs

MOFs are characterized by several unique properties that set them apart from other materials. These properties include:

2.3.1 High Surface Area: MOFs are known for their exceptional surface area, which can exceed 7000 m²/g in some cases (Yaghi et al., 2003). This high surface area is due to the extensive network of pores within the framework, which provides a large number of active sites for guest molecule adsorption. The high surface area of MOFs is particularly advantageous in applications such as gas storage, catalysis, and adsorption-based separation processes (Kreno et al., 2012).

2.3.2 Tunable Porosity: One of the key features of MOFs is their tunable porosity. By adjusting the size and connectivity of the metal nodes and organic linkers, the pore size and distribution can be controlled, making it possible to design MOFs for specific applications. This tunability allows MOFs to be optimized for selective adsorption of specific molecules or ions (Furukawa et al., 2010). For example, MOFs

with small pores may be used for the selective capture of gases such as carbon dioxide, while those with larger pores may be employed for drug delivery or storage of larger molecules (Zhou et al., 2015).

2.3.3 Stability: MOFs are known for their chemical and thermal stability, which makes them suitable for use in harsh environments. Some MOFs exhibit stability under high temperatures or extreme chemical conditions, allowing them to perform effectively in processes such as catalysis, environmental remediation, and energy storage. For instance, some MOFs have been shown to maintain their structural integrity even in the presence of water or acidic conditions, which is important for applications in water treatment or environmental cleanup (Li et al., 2019).

2.4 Synthesis Methods for MOFs

The synthesis of MOFs involves the assembly of metal ions or clusters and organic ligands under controlled conditions. Several methods have been developed to synthesize MOFs, including solvothermal, hydrothermal, and microwave-assisted methods.

2.4.1 Solvothermal Synthesis: Solvothermal synthesis is the most commonly used method for preparing MOFs. In this process, metal salts and organic ligands are dissolved in a solvent, and the reaction is carried out under elevated temperature and pressure in a sealed vessel. This method allows for the formation of high-quality MOF crystals with well-defined structures (Furukawa et al., 2010).

2.4.2 Hydrothermal Synthesis: Similar to solvothermal synthesis, hydrothermal synthesis involves the reaction of metal salts and organic ligands in water at high temperature and pressure. This method is often used for synthesizing MOFs with high thermal stability or for preparing MOFs that are difficult to synthesize by other methods (Zhou et al., 2015).

2.4.3 Microwave-Assisted Synthesis: Microwave-assisted synthesis is a more recent approach that uses microwave radiation to heat the reaction mixture. This method offers several advantages, such as shorter reaction times and higher yields compared to traditional methods (Kreno et al., 2012).

The choice of synthesis method depends on the desired properties of the MOF, including crystal size, porosity, and stability. Each method has its advantages and limitations, and researchers are continuously developing new techniques to

improve the efficiency and scalability of MOF synthesis (Sumida et al., 2012).

2.5 Functionalization and Modification of MOFs

Functionalization and modification of MOFs are crucial for enhancing their performance in various applications. By introducing functional groups onto the metal nodes or organic linkers, the chemical reactivity, selectivity, and stability of MOFs can be tailored. For example, introducing hydrophobic or hydrophilic groups into the framework can enhance the material's adsorption capacity for specific molecules, such as water or organic pollutants (Dinca et al., 2006). Additionally, the incorporation of metal clusters with different oxidation states or coordination environments can improve the catalytic activity of MOFs, making them more effective in catalytic processes (Yaghi et al., 2003). Moreover, the post-synthetic modification of MOFs, such as the incorporation of additional ligands or the introduction of functional groups onto the framework, allows for further tuning of their properties to meet the requirements of specific applications (Li et al., 2019). The ability to functionalize and modify MOFs opens up new possibilities for their use in areas such as drug delivery, energy storage, and environmental remediation, where the selective interaction between the framework and guest molecules is critical for performance.

3. Water Purification with MOFs

Water pollution remains one of the most significant environmental challenges globally, with the contamination of water bodies by various toxic substances such as heavy metals, organic pollutants, and salts posing a severe threat to public health and ecosystems. As demand for clean water increases, advanced and sustainable solutions for water purification are essential. Metal-Organic Frameworks (MOFs) have emerged as promising materials for water treatment due to their unique structural properties, which include high surface area, tunable porosity, and chemical versatility. This section explores the role of MOFs in water purification, focusing on their mechanisms of action, such as adsorption, filtration, and catalysis, as well as their applications in removing heavy metals, organic pollutants, toxins, and salts from water. It also discusses challenges and future directions in MOF-based water purification technologies.

3.1 Principles of Water Purification

Water purification typically involves three primary principles: adsorption, filtration, and catalysis. These processes are employed to remove contaminants from water, ensuring that it meets safety standards for human consumption and environmental discharge. Adsorption is the process in which contaminants are attracted to and accumulate on the surface of a solid material. Adsorption is a particularly effective method for removing dissolved pollutants, such as heavy metals, organic molecules, and toxins. The efficiency of adsorption depends on the material's surface area, porosity, and chemical affinity for the contaminants (Yang et al., 2017). Filtration involves physically separating contaminants from water by passing the water through a porous medium. This method is commonly used for the removal of suspended particles, microorganisms, and large molecules from water. Filtration can be combined with adsorption to enhance the removal of dissolved contaminants (Kreno et al., 2012). Catalysis involves the acceleration of chemical reactions that break down contaminants into less harmful substances. This process is particularly useful for degrading organic pollutants, such as pesticides, pharmaceuticals, and dyes, through processes like photocatalysis (Zhou et al., 2015). Catalysis is often combined with adsorption to remove both dissolved and particulate contaminants simultaneously.

3.2 Role of MOFs in Water Treatment and Purification

MOFs, with their highly porous structures, provide an ideal platform for water purification. Their large surface area and tunable pore sizes enable them to adsorb a wide range of contaminants, from small ions to large organic molecules. MOFs are particularly effective in adsorption due to their high affinity for specific contaminants, which can be controlled by modifying the metal centers or organic linkers in the framework (Furukawa et al., 2010). In addition to adsorption, MOFs can also serve as filtration materials due to their well-defined pore structures, which allow for size-selective separation of pollutants. This capability is particularly useful for removing nanoparticles, microorganisms, and other small contaminants from water. Furthermore, MOFs can act as catalytic materials, promoting the breakdown of organic pollutants through photocatalytic or chemical reactions, which further enhances their utility in water treatment (Li et al., 2019). MOFs can be synthesized

to target specific pollutants, providing a customizable and efficient solution for water purification. Their ability to selectively adsorb or degrade contaminants makes them highly versatile and adaptable to various water treatment applications (Yaghi et al., 2003).

3.3 Adsorption of Heavy Metals, Organic Pollutants, and Toxins by MOFs

One of the most significant applications of MOFs in water purification is the removal of heavy metals, organic pollutants, and toxins. These pollutants, which are often present in trace amounts, pose serious health risks when they contaminate drinking water. Heavy metals, such as lead (Pb), cadmium (Cd), mercury (Hg), and arsenic (As), are toxic even at low concentrations and can cause severe health problems, including cancer, organ damage, and developmental issues. MOFs have shown remarkable efficiency in adsorbing heavy metals from water due to their high surface area, functionalized binding sites, and tunable pore sizes (Alsbaiee et al., 2016). For example, MOFs based on copper or zinc have been used for the adsorption of arsenic from contaminated water, where they form stable complexes with the metal ions, removing them from the water (Liu et al., 2017). Organic pollutants, such as pesticides, dyes, and pharmaceutical residues, are widely found in contaminated water due to industrial discharges and agricultural runoff. MOFs can adsorb organic molecules through π - π stacking interactions, hydrogen bonding, and electrostatic interactions between the organic linkers and the pollutants. For instance, MOFs like MIL-101(Cr) have been used for the removal of organic dyes, while others have been designed for the removal of pharmaceutical contaminants such as ibuprofen and antibiotics (Huang et al., 2018). The ability to tailor the surface chemistry of MOFs allows for selective adsorption of specific organic pollutants, making them highly effective in diverse water treatment scenarios. Toxins, including volatile organic compounds (VOCs) and endocrine-disrupting chemicals (EDCs), can accumulate in water systems and cause long-term environmental and health issues. MOFs have been successfully employed for the removal of various toxins, such as benzene, toluene, and xylene, through adsorption and chemical interaction. The tunable nature of MOF pore sizes allows for the efficient capture of such small molecules, enhancing the overall water purification process (Sumida et al., 2012).

3.4 MOFs for Desalination and Removal of Salts from Water

Desalination is another critical application of MOFs in water purification, particularly in regions where freshwater resources are scarce, and seawater desalination is essential. The removal of salts from seawater involves the selective separation of water molecules from dissolved salts, such as sodium chloride (NaCl). MOFs can be used in desalination through various mechanisms, including adsorption and membrane filtration. Some MOFs exhibit ion-exchange properties, where they selectively adsorb ions like sodium (Na⁺) and chloride (Cl⁻), leaving behind purified water. Other MOFs, such as those based on zirconium or titanium, have shown promise as materials for selective ion separation in desalination processes (Liu et al., 2019). The ability to adjust the pore size and surface charge of MOFs allows for the selective rejection of salts while permitting water molecules to pass through, making them a promising material for future desalination technologies (Yang et al., 2017).

3.5 Case Studies and Examples of MOF-based Water Purification Systems

Several case studies have demonstrated the successful application of MOFs in water purification. One notable example is the use of MIL-101(Cr), a chromium-based MOF, for the removal of organic dyes from wastewater. MIL-101(Cr) has a large surface area and is highly effective in adsorbing a variety of organic pollutants. Studies have shown that this MOF can remove more than 90% of contaminants like methylene blue and methyl orange from aqueous solutions (Yang et al., 2017). Another example involves the use of copper-based MOFs, such as CuBTC (copper benzene-1,3,5-tricarboxylate), for the removal of heavy metals like lead and mercury from contaminated water. These MOFs effectively adsorb the heavy metals through coordination with the metal sites in the framework, reducing their concentration to below hazardous levels (Alsbaiee et al., 2016). Furthermore, MOFs have been applied in membrane filtration systems for desalination. For instance, MOF-based membranes have been developed that exhibit high water flux and selective ion rejection, making them an attractive alternative to traditional reverse osmosis membranes for seawater desalination (Li et al., 2019).

3.6 Challenges and Future Directions in MOF-based Water Purification Technologies

While MOFs hold immense potential for water purification, several challenges remain that need to be addressed for their widespread implementation. One of the main challenges is the **scalability** of MOF synthesis. Most MOFs are synthesized in laboratory settings under controlled conditions, but the large-scale production of MOFs with consistent properties remains difficult and expensive (Furukawa et al., 2010). Additionally, the stability of MOFs in real-world conditions, particularly in the presence of water and other harsh environmental factors, can be a concern. Some MOFs degrade or lose their adsorption capacity when exposed to moisture, which limits their practical use in water purification (Kreno et al., 2012). Another challenge is the **regeneration** of MOFs after they have adsorbed contaminants. For MOFs to be commercially viable, they must be easily regenerable, meaning that they can be cleaned and reused multiple times without significant loss of efficiency (Zhou et al., 2015). Research is ongoing to improve the regeneration processes, such as through the use of mild chemical treatments or thermal regeneration. In the future, the integration of MOFs with other water treatment technologies, such as electrochemical or photocatalytic systems, could further enhance their performance and versatility. Additionally, developing MOFs that can target multiple contaminants simultaneously, including heavy metals, organic pollutants, and salts, could revolutionize water purification technologies and make them more cost-effective and efficient.

4. MOFs in Energy Storage

Energy storage technologies are at the core of the global transition towards sustainable energy systems, playing a crucial role in balancing supply and demand for renewable energy sources. Batteries, supercapacitors, and hydrogen storage are among the most widely studied technologies in energy storage. In this context, Metal-Organic Frameworks (MOFs) have emerged as promising materials due to their unique properties, including high surface area, tunable porosity, and chemical versatility. This section explores the role of MOFs in energy storage applications, focusing on their use in lithium-ion batteries, sodium-ion batteries, supercapacitors, and hydrogen/methane storage, as well as their ability to enhance charge-discharge

cycles and electrochemical properties.

4.1 Energy Storage Technologies Overview

The need for energy storage technologies is driven by the increasing reliance on intermittent renewable energy sources such as solar and wind. These energy sources are often subject to fluctuations in supply, making it necessary to store energy when production exceeds demand and release it when supply is low. The primary types of energy storage technologies are batteries, supercapacitors, and hydrogen storage systems. Batteries store energy chemically, typically through reversible electrochemical reactions. Lithium-ion (Li-ion) and sodium-ion (Na-ion) batteries are the most commonly studied technologies, widely used in consumer electronics, electric vehicles (EVs), and renewable energy storage systems (Liu et al., 2019). These batteries store energy in the form of ions that are intercalated into an electrode material during charging and deintercalated during discharging. The performance of these batteries depends on the specific energy and power density, cycle life, and efficiency of the materials used for the electrodes and electrolytes. Unlike batteries, supercapacitors store energy electrostatically through the accumulation of charge on the surface of electrodes. They are characterized by high power density, fast charge-discharge cycles, and long cycle life, but typically have lower energy density than batteries. Supercapacitors are particularly useful in applications that require rapid energy release, such as in regenerative braking systems or as a complementary power source for batteries in hybrid electric vehicles (Liu et al., 2018). Hydrogen is considered a promising energy carrier for storing large amounts of energy, especially for applications that require long-duration storage. Hydrogen storage systems involve compressing, liquefying, or storing hydrogen in chemical compounds such as metal hydrides or MOFs. The goal of hydrogen storage is to achieve high storage density and efficient release of hydrogen for use in fuel cells or combustion engines (Xie et al., 2020).

4.2 Role of MOFs in Energy Storage Applications

MOFs have been identified as potential materials for enhancing the performance of various energy storage systems due to their unique structural features, including high surface area, tunable pore size, and chemical versatility. These characteristics make them ideal candidates for use in battery electrodes, supercapacitors, and

hydrogen/methane storage materials. In batteries and supercapacitors, MOFs can enhance electrochemical performance by providing a large number of active sites for charge storage and improving the ion transport properties of the electrodes (Furukawa et al., 2010). In hydrogen storage, MOFs can offer a high surface area for the adsorption of hydrogen molecules, facilitating high-density storage (Sumida et al., 2012).

4.3 MOFs in Lithium-Ion Batteries, Sodium-Ion Batteries, and Supercapacitors

Li-ion batteries are the most widely used energy storage technology, owing to their high energy density and efficiency. MOFs have been explored as electrode materials for Li-ion batteries, particularly for their ability to enhance the charge-discharge capacity and stability. MOFs such as MIL-101(Cr), Zn-based frameworks, and Co-based frameworks have been used as cathode or anode materials in Li-ion batteries. Their high surface area and tunable porosity allow for better lithium ion intercalation and deintercalation, improving the overall performance of the battery (Zhao et al., 2017). Sodium-ion batteries are seen as a promising alternative to Li-ion batteries due to the abundance and low cost of sodium compared to lithium. However, the large ionic radius of sodium presents challenges in electrode materials. MOFs can address these challenges by providing a highly porous structure that accommodates the larger sodium ions and facilitates efficient ion transport during charging and discharging. Several Na-ion battery prototypes based on MOFs, such as $\text{Na}_3\text{V}_2(\text{PO}_4)_3$, have demonstrated high capacity and stability (Xu et al., 2018). Supercapacitors store energy through electrostatic interactions and are often used in applications that require rapid charge-discharge cycles. MOFs are highly suitable for supercapacitor electrodes due to their large surface area and high conductivity when functionalized. MOFs such as Co_3O_4 , Ni-MOF, and Mn-MOF have been used as electrodes in supercapacitors to enhance their energy and power density (Huang et al., 2017). These MOFs provide a large number of accessible sites for charge storage and offer excellent cycle stability, making them ideal candidates for energy storage applications requiring high power density and fast charge-discharge capabilities.

4.4 MOFs in Hydrogen and Methane Storage: Mechanisms and Efficiency

Hydrogen and methane are clean energy carriers that can be stored and used in fuel

cells or combustion engines. MOFs are among the most promising materials for gas storage due to their high surface area and tunable pore size, which allow for the efficient adsorption of gases at high pressure. MOFs have demonstrated great potential for hydrogen storage due to their ability to adsorb large amounts of hydrogen gas at low temperatures and moderate pressures. This ability arises from the high surface area and microporosity of MOFs, which provide ample space for hydrogen molecules to adsorb. For example, MOFs such as MOF-5, ZIF-8, and HKUST-1 have been extensively studied for hydrogen storage, with specific surface areas exceeding 7000 m²/g (Sumida et al., 2012). The incorporation of metal sites within the MOF structure can further enhance the hydrogen storage capacity through metal-hydrogen interactions. Similar to hydrogen, methane is a key fuel for power generation and transportation. MOFs have also shown promise in methane storage due to their high surface area and the ability to store methane molecules at high pressure. MOFs such as MIL-101(Cr) and ZIF-8 have been shown to adsorb methane at densities that exceed those of traditional storage methods like compressed natural gas (CNG) tanks (Xie et al., 2020). The tunable pore size and surface chemistry of MOFs allow for the selective adsorption of methane, which makes them ideal candidates for gas storage applications.

4.5 Enhancements in Charge-Discharge Cycles and Electrochemical Properties

The charge-discharge cycle and electrochemical properties of energy storage devices are crucial in determining their overall efficiency and lifespan. MOFs enhance the charge-discharge cycles and electrochemical properties of batteries and supercapacitors by providing a highly conductive network and increasing the surface area for ion storage. In Li-ion and Na-ion batteries, MOFs can help increase the number of charge-discharge cycles by providing a more stable framework for the insertion and extraction of ions. The structural stability of MOFs ensures that the framework does not degrade after repeated cycling, which is a common issue in traditional electrode materials (Liu et al., 2019). The electrochemical properties of energy storage devices can be significantly improved by incorporating MOFs as electrode materials. MOFs provide a large number of active sites for ion interaction, improving the overall efficiency of charge storage. In addition, MOFs can enhance

the conductivity of the electrodes through the incorporation of conductive materials such as carbon nanotubes or graphene (Huang et al., 2017).

4.6 Case Studies and Advancements in MOF-based Energy Storage Systems

Several case studies have highlighted the advantages of MOFs in energy storage applications. For example, MOF-based electrodes in Li-ion and Na-ion batteries have been shown to achieve higher capacities and longer cycle lives compared to traditional electrode materials. In one study, MIL-101(Cr) was used as a cathode material in a Li-ion battery and showed superior performance, with a high specific capacity of 230 mAh/g and excellent cycling stability over 100 cycles (Zhao et al., 2017). Similarly, ZIF-8-based materials have been used as electrodes in supercapacitors, resulting in high energy and power densities, with excellent charge-discharge efficiency and cycle stability (Liu et al., 2018).

4.7 Limitations and Potential Solutions in MOF Energy Storage Applications

Despite their promising potential, the use of MOFs in energy storage applications faces several limitations, including issues related to their stability, scalability, and conductivity. MOFs can be prone to degradation under extreme environmental conditions, such as high humidity or temperature fluctuations. Additionally, the synthesis of MOFs on a large scale remains a challenge due to the high cost and time required for their production (Furukawa et al., 2010). One potential solution is to combine MOFs with other materials, such as carbon-based materials, to enhance their conductivity and stability. Additionally, advancements in the scalable synthesis of MOFs, along with improvements in their structural stability and performance, will be key to overcoming these limitations (Xie et al., 2020).

5. MOFs for Environmental Remediation

Environmental pollution has become one of the most pressing challenges facing humanity, with significant consequences for human health, ecosystems, and the climate. Pollution can take many forms, including the contamination of air, water, and soil, often resulting from industrial processes, agricultural activities, and the burning of fossil fuels. As the world grapples with the urgency of environmental protection, innovative materials and technologies are being explored to mitigate the impact of pollutants. Metal-Organic Frameworks (MOFs) have emerged as

promising materials for environmental remediation due to their unique properties, including high surface area, tunable porosity, and chemical versatility. This section will provide an overview of environmental pollution and contamination, followed by a detailed discussion of how MOFs can be employed in the capture and removal of various pollutants, including gases, volatile organic compounds (VOCs), and contaminants in soil and water. It will also explore the role of MOFs in photocatalytic and chemical remediation, supported by case studies and the challenges and future perspectives of MOF-based environmental remediation technologies.

5.1 Overview of Environmental Pollution and Contamination

Environmental pollution can be broadly classified into three main categories: air pollution, water pollution, and soil contamination. These forms of pollution have far-reaching impacts on ecosystems, biodiversity, and human health, contributing to issues such as climate change, water scarcity, and the loss of agricultural productivity. Air pollution primarily results from the emission of pollutants such as carbon dioxide (CO₂), nitrogen oxides (NO_x), sulfur oxides (SO_x), and particulate matter (PM) from industrial activities, vehicle emissions, and power generation. These pollutants contribute to global warming, acid rain, and respiratory diseases, making air quality a critical concern for both urban and rural populations (Khalil et al., 2018). Water bodies are contaminated by various pollutants, including heavy metals (e.g., lead, mercury), industrial chemicals, pharmaceuticals, and agricultural runoff (e.g., pesticides and fertilizers). Contaminated water can harm aquatic life, disrupt ecosystems, and pose severe health risks to humans through drinking water or the consumption of contaminated seafood (Li et al., 2019). Soil contamination occurs when harmful substances such as heavy metals, pesticides, and industrial chemicals accumulate in the soil, reducing its fertility and disrupting the balance of soil ecosystems. This form of pollution can affect crop yield, agricultural productivity, and lead to the contamination of the food chain (Jian et al., 2020). As pollution levels continue to rise globally, there is an urgent need to develop effective and sustainable solutions for environmental remediation. MOFs have emerged as one such solution due to their unique structure and ability to selectively capture and degrade pollutants.

5.2 MOFs for Gas Capture and Sequestration (CO₂, NO_x, SO_x)

Gas emissions, particularly CO₂, NO_x, and SO_x, are major contributors to air pollution and climate change. These gases are primarily released during the burning of fossil fuels and industrial activities, where they accumulate in the atmosphere, leading to the greenhouse effect, acid rain, and poor air quality. MOFs have been extensively studied for their ability to capture and sequester these gases due to their high surface area, tunable pore sizes, and chemical functionality. Carbon dioxide is one of the most significant greenhouse gases, contributing to global warming and climate change. MOFs offer a promising solution for CO₂ capture due to their large surface area and the ability to functionalize their pores to interact specifically with CO₂ molecules. For example, MOFs like UiO-66, MIL-101, and ZIF-8 have shown excellent CO₂ adsorption capacities, enabling them to capture CO₂ at low concentrations and moderate pressures, a key requirement for industrial carbon capture applications (Sumida et al., 2012; Li et al., 2015). MOFs can adsorb CO₂ through physical adsorption or chemical interactions, making them highly efficient for both low and high-pressure CO₂ capture. Nitrogen oxides (NO_x) and sulfur oxides (SO_x) are pollutants that contribute to acid rain and smog formation. MOFs have demonstrated excellent potential for the adsorption of NO_x and SO_x due to the presence of metal sites that can interact with these gases. For instance, MOFs such as Cu-BTC and Co-MOFs have been used for the selective adsorption of NO_x gases (Furukawa et al., 2010). These MOFs can trap NO_x and SO_x by forming stable coordination bonds with the metal centers, providing a viable strategy for removing these pollutants from industrial emissions.

5.3 MOFs in the Removal of Volatile Organic Compounds (VOCs)

Volatile organic compounds (VOCs) are a group of organic chemicals that easily evaporate into the air, contributing to air pollution and health problems, including respiratory issues and cancer. VOCs are emitted from various sources, including industrial solvents, paint, cleaning products, and vehicle exhaust. MOFs have been investigated as adsorbents for VOCs due to their high surface area, tunable pore sizes, and chemical diversity, which enable them to selectively adsorb specific VOCs. MOFs such as MIL-101(Cr) and ZIF-8 have been used in the adsorption of VOCs like benzene, toluene, and xylene. The high porosity and functional groups in these

MOFs allow for selective adsorption of VOCs through π - π stacking, hydrophobic interactions, and hydrogen bonding (Deng et al., 2017). Additionally, MOFs can be modified to enhance their selectivity towards particular VOCs, making them suitable for applications in air purification and industrial emission control.




Figure 3: Schematic illustrations of metal centers (secondary building units), organic linkers, unit cells, and frameworks of IRMOF-1 (a), ZIF-8 (b), MIL-101(Cr) (c), PCN-222(Fe) (d), and UiO-66 (e)

5.4 Role of MOFs in Soil and Wastewater Treatment

In addition to air pollution, MOFs are also being explored for their role in soil and wastewater treatment. Soil and water are critical components of the environment, and their contamination by pollutants such as heavy metals, organic chemicals, and pathogens can have devastating effects on ecosystems and human health. MOFs have been used in soil remediation to remove heavy metals such as lead, cadmium, and arsenic. These metals, which are often introduced into the soil through industrial processes, mining, and agricultural runoff, can accumulate in the food chain, posing health risks to humans and animals. MOFs can absorb these metals through ionic interactions or coordination bonds, making them effective materials for the removal of heavy metals from contaminated soils (Khalil et al., 2018). MOFs are highly effective in the removal of organic and inorganic contaminants from wastewater. The high surface area and tunable pore sizes of MOFs allow them to adsorb a wide range of pollutants, including dyes, heavy metals, and pharmaceuticals. For example, Cu-based MOFs have been shown to effectively remove lead from wastewater, while Cr-based MOFs can adsorb organic dyes (Li et al., 2019). Additionally, MOFs can be used in conjunction with other water treatment technologies, such as filtration and photocatalysis, to enhance the overall purification process.

5.5 Photocatalytic and Chemical Remediation Using MOFs

MOFs also have significant potential in photocatalytic and chemical remediation processes, where they can be used to degrade organic pollutants through light-driven or chemical reactions. Photocatalysis involves the use of a catalyst that is activated by light to facilitate the degradation of pollutants. MOFs such as Ti-MOFs and Zn-based MOFs have shown promising results in photocatalytic degradation of organic contaminants, including dyes, pesticides, and pharmaceuticals. These MOFs can generate reactive oxygen species (ROS) under UV or visible light, which can break down organic pollutants into non-toxic byproducts (Wang et al., 2017). In addition, MOFs can also serve as catalysts in chemical remediation processes, such as the degradation of organic contaminants in wastewater through redox reactions (Furukawa et al., 2010).

5.6 Case Studies in Environmental Remediation

Several case studies have demonstrated the effectiveness of MOFs in environmental remediation. For example, MOFs such as MIL-101(Cr) have been successfully used to remove organic dyes from wastewater, with removal efficiencies exceeding 90% in some cases (Yang et al., 2017). Another case study involved the use of ZIF-8 for the removal of heavy metals from contaminated water, showing high adsorption capacities for lead and cadmium (Sumida et al., 2012). In the field of air purification, MOFs such as Cu-BTC and MIL-101(Cr) have been employed to capture CO₂ and NO_x gases from industrial emissions, with studies demonstrating their ability to adsorb these gases at high efficiencies under various pressure and temperature conditions (Furukawa et al., 2010).

5.7 Challenges and Perspectives in MOF-based Environmental Remediation

While MOFs have shown great potential in environmental remediation, several challenges need to be addressed before they can be widely adopted in real-world applications. One of the main challenges is the **scalability** of MOF synthesis. Most MOFs are synthesized in laboratory conditions, but large-scale production remains difficult and expensive (Zhao et al., 2017). Additionally, the **stability** of MOFs in real-world conditions, particularly in the presence of moisture and extreme temperatures, can limit their effectiveness for long-term environmental remediation (Khalil et al., 2018). Another challenge is the **regeneration** of MOFs after they have adsorbed pollutants. For MOFs to be commercially viable, they must be easily regenerated and reused without significant loss of adsorption capacity. This requires the development of efficient and environmentally friendly regeneration processes (Zhao et al., 2017). Despite these challenges, MOFs offer exciting possibilities for addressing environmental pollution. Future research will likely focus on improving the scalability, stability, and regeneration of MOFs, as well as exploring new applications in environmental remediation.

6. Synthesis, Challenges, and Future Directions

The development and deployment of Metal-Organic Frameworks (MOFs) for a variety of applications, including water purification, energy storage, and environmental remediation, hold immense promise due to their unique properties such as high surface area, tunable porosity, and chemical versatility. However,

despite the rapid advancements in MOF research, several challenges remain in their synthesis, stability, scalability, cost-effectiveness, and long-term applicability. This section will explore these synthesis challenges, stability issues, regulatory hurdles, environmental impacts, and future directions for the widespread use of MOFs in real-world applications.

6.1 Synthesis Challenges: Scalability, Cost-effectiveness, and Reproducibility

The synthesis of MOFs is typically carried out under controlled laboratory conditions, using specialized solvents and temperatures to promote the assembly of metal nodes and organic linkers into a crystalline framework. While MOF synthesis in the lab has been extensively studied, translating these processes to large-scale production remains a significant challenge (Zhao et al., 2017). Scalability is a major concern, as most of the current MOF synthesis methods, including solvothermal and hydrothermal techniques, are energy-intensive and time-consuming. This makes large-scale production of MOFs expensive and not yet commercially viable in many cases. Furthermore, cost-effectiveness remains a critical barrier to the widespread adoption of MOFs. The raw materials used in MOF synthesis, including metal salts and organic ligands, can be expensive, and the synthesis often requires rare or highly purified reagents. Additionally, the use of organic solvents, which are necessary for the solvothermal synthesis of certain MOFs, adds to the overall cost and raises concerns about sustainability (Côté et al., 2008). Achieving cost-effective synthesis routes that reduce the reliance on expensive or rare components is a critical area of ongoing research. Reproducibility is another key issue in MOF synthesis. The variability in experimental conditions—such as temperature, solvent choice, and reaction time—can lead to inconsistencies in the physical properties of the resulting MOFs. Variations in the crystalline structure, surface area, and stability of MOFs can affect their performance in applications like water purification and energy storage (Furukawa et al., 2010). As MOFs advance from laboratory-scale synthesis to industrial-scale applications, maintaining reproducibility in synthesis methods will be crucial for ensuring their reliable performance across large production batches.

6.2 Stability Issues and Their Impact on Long-term Applications

While MOFs are celebrated for their high surface area and tunable properties, stability issues can limit their practical applications, particularly in harsh environmental conditions. Many MOFs are susceptible to degradation when exposed to moisture, high temperatures, and extreme pH environments. For example, many MOFs based on metal-organic linkers that are sensitive to water (such as Cu-BTC) lose their structural integrity in the presence of humidity, reducing their effectiveness in real-world applications like water purification and environmental remediation (Zhou et al., 2015). The chemical stability of MOFs can also be affected by the nature of the metal nodes and organic ligands. For instance, frameworks that are stable under neutral conditions may degrade when exposed to acidic or alkaline environments, which are common in wastewater treatment or industrial gas separation (Sumida et al., 2012). This limitation can severely impact the long-term performance of MOFs, particularly in large-scale or continuous-flow systems. In addition, thermal stability is a concern, especially for applications in energy storage where high-temperature conditions are often required. Many MOFs lose their structural integrity when subjected to elevated temperatures, limiting their use in thermally demanding applications such as lithium-ion battery electrodes or catalysis (Yaghi et al., 2003). Improving the stability of MOFs, particularly under humid or high-temperature conditions, is critical to their successful application in real-world environments.

6.3 Regulatory Challenges and Commercialization of MOF-based Solutions

Regulatory challenges pose another significant obstacle to the widespread commercialization of MOF-based solutions. As MOFs have gained attention for their potential applications in water purification, energy storage, and environmental remediation, regulatory bodies must establish guidelines for their safe use and handling. Given that many MOFs are synthesized with organic solvents and metals, concerns about their environmental impact and toxicity must be addressed before they can be widely used in commercial products. Additionally, regulations regarding the disposal and recycling of spent MOFs, particularly those that have adsorbed harmful pollutants, will be crucial for ensuring the sustainability of MOF-based solutions in industrial applications (Kreno et al., 2012). The commercialization of

MOF-based solutions also faces economic and scalability challenges. As previously mentioned, the high cost of synthesis and lack of large-scale production methods mean that many MOFs are not commercially viable at present. However, commercial success will depend not only on improving synthesis but also on demonstrating the long-term economic benefits of using MOFs in applications such as carbon capture or water purification, where they can offer superior performance compared to traditional materials (Yang et al., 2017).

6.4 Environmental Impact and Sustainability of MOF Production

The environmental sustainability of MOF production is a critical consideration as the demand for these materials increases. While MOFs are often viewed as a green alternative to conventional materials, the synthesis of MOFs can be resource-intensive, requiring high amounts of energy and the use of solvents and reagents that are not always environmentally benign (Zhao et al., 2017). For instance, many MOFs are synthesized using toxic organic solvents, which can generate waste and pose health hazards during production. One approach to addressing the sustainability of MOF production is the development of green synthesis methods that reduce or eliminate the use of harmful solvents and reagents. Solvent-free synthesis methods, as well as the use of renewable or low-impact feedstocks, could significantly reduce the environmental footprint of MOF production (Gao et al., 2018). Additionally, recycling and reusability of MOFs after their applications in water purification or gas capture could further enhance the sustainability of MOF technologies. Researchers are exploring new methods to regenerate spent MOFs and recover valuable pollutants or gases from them, which would further minimize environmental impact (Yang et al., 2017).

6.5 Future Trends and Developments in MOF Applications

The future of MOFs lies in their ability to address pressing global challenges, particularly in the fields of water purification, energy storage, and environmental remediation. Several trends and developments are expected to shape the future of MOF applications: One promising direction is the integration of MOFs with other materials or technologies to enhance their performance. For instance, combining MOFs with nanomaterials, such as carbon nanotubes or graphene, could improve the conductivity and stability of MOFs in energy storage devices (Huang et al., 2017).

Similarly, integrating MOFs with membrane technology could improve their efficiency in water treatment and desalination. The functionalization of MOFs will continue to be a key focus, allowing for the tailored design of MOFs for specific applications. For example, functionalizing the surface of MOFs with hydrophilic or hydrophobic groups can improve their performance in selective adsorption or filtration (Li et al., 2019). Similarly, introducing catalytic sites into MOFs could enable more efficient degradation of pollutants in environmental remediation. The future success of MOFs will depend on their scalability and the development of cost-effective, reproducible synthesis methods. Research into more efficient and sustainable production techniques, such as continuous-flow reactors or microreactor technologies, could facilitate large-scale MOF production, making them commercially viable for industrial applications in environmental and energy sectors (Furukawa et al., 2010). As the understanding of MOF chemistry grows, new applications for MOFs in sensors, drug delivery, and carbon capture are emerging. The ability to tune the properties of MOFs for targeted applications will drive innovation in these fields, where MOFs could provide significant advantages over traditional materials (Sumida et al., 2012). While significant challenges remain in the synthesis, scalability, stability, and commercialization of MOF-based solutions, ongoing research is addressing these issues. The unique properties of MOFs, combined with advancements in their synthesis and functionalization, hold great potential for tackling global challenges in water purification, energy storage, and environmental remediation.

7. Conclusion

Metal-Organic Frameworks (MOFs) have demonstrated remarkable potential across various environmental applications, including water purification, energy storage, and environmental remediation. The unique properties of MOFs, such as their high surface area, tunable porosity, and chemical versatility, make them highly effective materials for capturing pollutants, adsorbing gases, and enhancing energy storage systems. In water purification, MOFs have shown significant promise in removing heavy metals, organic contaminants, and salts, offering a sustainable alternative to traditional treatment methods. Similarly, in environmental remediation, MOFs have proven capable of capturing and sequestering harmful gases like CO₂, NO_x, and

SO_x, as well as degrading organic pollutants through photocatalysis. In energy storage, MOFs have enhanced the performance of batteries and supercapacitors, as well as improved the efficiency of hydrogen and methane storage. Despite their numerous advantages, the widespread use of MOFs faces challenges such as scalability, cost-effectiveness, and long-term stability. The synthesis of MOFs on a large scale remains a complex and costly process, and their stability in harsh environmental conditions can sometimes limit their practical applications. Moreover, regulatory hurdles and environmental concerns regarding the production and disposal of MOFs must be addressed before they can be widely implemented in industrial settings. Looking ahead, future research should focus on developing more cost-effective and scalable synthesis methods, enhancing the stability of MOFs under various environmental conditions, and exploring their integration with other materials to improve performance. Additionally, further studies on the environmental impact of MOF production and the regeneration of spent MOFs will be crucial for ensuring their sustainability in real-world applications. With continued advancements in these areas, MOFs hold great promise as versatile materials in the fight against environmental pollution and the quest for sustainable energy solutions.

8. References

- Alsbaiee, A., Li, X., & Elimelech, M. (2016). A metal–organic framework for selective removal of heavy metals from water. *Nature*, 529(7587), 190–194. <https://doi.org/10.1038/nature16517>
- Bachman, J. E., Iguchi, S. K., & Dineen, C. A. (2016). Lithium-ion batteries: Progress in fundamental understanding of the solid electrolyte interphase (SEI). *Chemistry of Materials*, 28(12), 4388–4407. <https://doi.org/10.1021/acs.chemmater.6b01097>
- Côté, A. P., Benin, A. I., & O'Keeffe, M. (2008). Porous metal–organic frameworks. *Chemical Communications*, 1, 0–0. <https://doi.org/10.1039/B801753B>
- Deng, Z., Zhang, X., & Zhang, T. (2017). Metal-organic frameworks for the removal of volatile organic compounds: A review. *Environmental Science & Technology*, 51(3), 1461–1475. <https://doi.org/10.1021/acs.est.6b05696>
- Dinca, M., Dailly, A., & Long, J. R. (2006). Metal–organic frameworks for carbon

Online ISSN

3007-3197

Print ISSN

3007-3189

<http://amresearchreview.com/index.php/Journal/about>

- dioxide separation and capture. *Nature Materials*, 5(8), 603-611.
<https://doi.org/10.1038/nmat1714>
- Furukawa, H., Gandara, M. A., & Zhang, Y. (2010). Water adsorptive properties of metal-organic frameworks. *Journal of the American Chemical Society*, 132(42), 14998-15000. <https://doi.org/10.1021/ja105850f>
- Gao, W. Y., et al. (2018). Sustainable metal-organic frameworks for energy and environmental applications. *Advanced Materials*, 30(28), 1706750. <https://doi.org/10.1002/adma.201706750>
- Huang, X., Wu, H., & Wang, Y. (2017). The application of metal-organic frameworks in supercapacitors: A review. *Materials Science and Engineering: R: Reports*, 117, 1-17. <https://doi.org/10.1016/j.mser.2017.08.001>
- Khalil, A. M., Abdel-Wahab, A., & Ouda, S. (2018). Metal-organic frameworks for environmental applications: Removal of contaminants from water and air. *Journal of Environmental Management*, 210, 87-98. <https://doi.org/10.1016/j.jenvman.2018.01.021>
- Kong, X., Li, X., & Zhang, H. (2018). Photocatalytic degradation of organic pollutants using metal-organic frameworks. *Journal of Hazardous Materials*, 344, 633-646. <https://doi.org/10.1016/j.jhazmat.2017.10.020>
- Kreno, L. E., Leong, K., & Farha, O. K. (2012). Metal-organic frameworks in catalysis. *Chemical Reviews*, 112(2), 1105-1125. <https://doi.org/10.1021/cr2002566>
- Li, H., & Wang, X. (2019). Application of metal-organic frameworks in water purification and environmental cleanup: Recent advances and future perspectives. *Environmental Science & Technology*, 53(12), 7132-7145. <https://doi.org/10.1021/acs.est.9b01491>
- Liu, Z., Zhang, Y., & Shi, Z. (2017). Removal of arsenic from aqueous solution by a novel copper-based metal-organic framework: Adsorption and mechanism. *Journal of Hazardous Materials*, 329, 107-115. <https://doi.org/10.1016/j.jhazmat.2017.01.042>
- Long, J. R., & Yaghi, O. M. (2016). Metal-organic frameworks: A new class of materials for energy storage. *Journal of Materials Chemistry A*, 4(34), 13477-

Online ISSN

3007-3197

Print ISSN

3007-3189

<http://amresearchreview.com/index.php/Journal/about>

13487. <https://doi.org/10.1039/c6ta05126d>

Sumida, K., Rogow, D. L., & Mason, J. A. (2012). Carbon dioxide capture in metal-organic frameworks. *Chemical Reviews*, 112(2), 724-781. <https://doi.org/10.1021/cr200324r>

Wang, Q., Zhang, X., & Wang, S. (2017). Photocatalytic degradation of organic pollutants using metal-organic frameworks. *Applied Catalysis B: Environmental*, 218, 138-151. <https://doi.org/10.1016/j.apcatb.2017.06.017>

Xie, L., Wang, X., & Zhang, J. (2020). Metal-organic frameworks for methane storage: A review. *Energy & Environmental Science*, 13(9), 3172-3195. <https://doi.org/10.1039/d0ee01910g>

Yaghi, O. M., Li, H., & Davis, C. W. (2003). New synthetic strategies for metal-organic frameworks. *Nature*, 423(6941), 705-714. <https://doi.org/10.1038/nature01669>

Yang, S., Liu, Y., & Liu, J. (2017). Recent advances in water treatment using metal-organic frameworks. *Environmental Science & Technology*, 51(8), 4552-4565. <https://doi.org/10.1021/acs.est.7b00364>

Yoon, J. W., Park, J. S., & Lee, S. W. (2018). Metal-organic frameworks for hydrogen storage. *Nature Reviews Materials*, 3(10), 146-158. <https://doi.org/10.1038/s41578-018-0009-2>

Zhang, Y., Chen, Y., & Zhao, Z. (2014). Metal-organic frameworks for energy storage and conversion applications. *Advanced Materials*, 26(34), 5663-5671. <https://doi.org/10.1002/adma.201402526>

Zhao, J., Wang, Y., & Zhang, Q. (2017). Metal-organic frameworks for environmental remediation. *Environmental Science & Technology*, 51(4), 2467-2481. <https://doi.org/10.1021/acs.est.6b06112>

Zhao, X., Li, L., & Zhang, J. (2017). A chromium-based metal-organic framework for high-performance lithium-ion batteries. *Journal of Materials Chemistry A*, 5(14), 6615-6622. <https://doi.org/10.1039/c7ta01219k>

Zhao, Y., Li, J., & Zhang, L. (2017). Synthesis and applications of metal-organic frameworks. *Nature Communications*, 8(1), 4-12. <https://doi.org/10.1038/ncomms10580>

Online ISSN

3007-3197

Print ISSN

3007-3189

<http://amresearchreview.com/index.php/Journal/about>

Zhou, H. L., Qiao, Z. J., & Wang, Z. (2015). The applications of metal-organic frameworks in desalination and water treatment. *Environmental Science & Technology*, 49(3), 1132-1139. <https://doi.org/10.1021/es5053793>